

**Product Data Sheet**  
Edition 08/11/05  
Identification no:  
010302060020000001  
Sikadur®-52 ZA

# Sikadur®-52 ZA

## Low viscosity injection resins

### Product Description

Sikadur®-52 ZA is a two part, solvent-free, low viscosity injection-liquid, based on high strength epoxy resins.

### Uses

As an injection resin with good adhesion to concrete, mortar, stone, steel and wood. Sikadur®-52 ZA is used to fill and seal voids and cracks in structures such as bridges and other civil engineering buildings, industrial and residential buildings, e.g. columns, beams, foundations, walls, floors and water retaining structures. It not only forms an effective barrier against water infiltration and corrosion promoting media, but it also structurally bonds the concrete sections together.

### Characteristics / Advantages

- Solvent-free
- Suitable for both, dry and damp conditions
- Usable at low temperatures
- Shrinkage free hardening
- High mechanical and adhesive strengths
- Hard but not brittle
- Low viscosity
- Injectable with single component pumps

### Product Data

#### Form

<b>Colours</b>	Part A:	Transparent
	Part B:	Brownish
	Part A+B mixed:	Yellowish-brownish

<b>Packaging</b>	Pre batched:
	Part A+B: 1.5 Litre and 75 Litre containers



---

**Storage**

---

**Storage Conditions/  
Shelf-Life** 12 months from date of production if stored properly in unopened, undamaged and sealed original packaging, in dry conditions at temperatures between +5°C and +30°C.

---

**Technical Data**

---

**Chemical Base** Modified solvent-free two-part epoxy resin.

---

**Density** Part A+B mixed : 1.1 kg/l (at +20°C)

---

**Viscosity**

Temperature	Part A+B mixed
+10°C	~ 1200 cps
+20°C	~ 430 cps
+30°C	~ 220 cps
+40°C	-

---

**Mechanical / Physical  
Properties**

---

**Compressive Strength** 52 N/mm<sup>2</sup> (after 7 days at +23°C) (According to ASTM D695-96)

---

**Flexural Strength** 61 N/mm<sup>2</sup> (after 7 days at +23°C) (According to DIN 53452)

---

**Tensile Strength** 37 N/mm<sup>2</sup> (after 7 days at +23°C) (According to ISO 527)

---

**Bond Strength** To concrete:  
> 4 N/mm<sup>2</sup> (failure in concrete) (after 7 days at +23°C)

---

**System Information**

---

**Application Details**

---

**Consumption / Yield** 1kg of Sikadur<sup>®</sup>-52 ZA are ~ equal to 1 litre injection resin.

---

**Substrate Preparation** Requirements:  
Sound, clean, free from oil and grease, old coatings and surface treatments, etc.  
  
Pre-treatment for good bond:  
Concrete, mortar, stone should be thoroughly prepared by high pressure water jetting or mechanical means such as grinding, chiselling, etc. Cracks must be cleaned to remove dust with compressed air.

---

**Application  
Conditions /  
Limitations**

---

**Substrate Temperature** +5°C min. / +30°C max.

---

**Substrate Humidity** Dry or damp SSD – (Saturated Surface Dry: no standing water)

---

**Application  
Instructions**

---

**Mixing**

---

**Mixing Time** Pre-batched packaging:  
Add all of part B to part A. Mix with an electric mixer at slow speed (max. 250 rpm) for at least 3 minutes. Avoid entraining air.  
  
Bulk packaging:  
Add both parts in the correct proportion into a suitable clean, dry container and mix in the same way as for the prebatched units.

---

**Application Method / Tools**

Cracks in horizontal slabs:  
Saturate a few times using a brush or gravity fill them by pouring mixed Sikadur®-52 ZA between two “dams” e.g. made from Sikaflex® sealant. Cracks penetrating slabs to their soffit should first be sealed on the underside, e.g. with Sikadur®-31 epoxy mortar.

Cracks in vertical structures:  
Mixed Sikadur®-52 ZA can be injected under pressure into the cracks using a single component injection pump, such as the Aliva AL-1200, AL-1250 or the Sika® Hand Pump. Injection ports (packers) are set at approx. 25 cm intervals beside the crack and the crack between the injection ports (packers) sealed e.g. with Sikadur®-31 to prevent injection resin to escape during the injection process. Vertical cracks should always be injected from the bottom upwards. As soon as injection resin oozes out of the next packer / injection port, the first one is sealed and the injection process continued from the next one.  
After completion of the injection process, the injection ports (packers) as well as the sealing material between the ports are removed.

**Cleaning of Tools**

Clean all tools and application equipment with Sika® Kwiklean immediately after use. Hardened / cured material can only be mechanically removed.

**Potlife**

Temperature	(1 litre mixture)
+5°C	~ 120 minutes
+10°C	~ 80 minutes
+23°C	~ 25 minutes
+30°C	~ 10 minutes
+40°C	-

**Notes on Application / Limitations**

Maximum width of cracks to be injected: 5 mm.  
Sikadur®-52 ZA is suitable for dry and damp, but not for wet injection conditions.

**Notes**

All technical data stated in this Product Data Sheet is based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

**Local Restriction**

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the product uses.

**Health and Safety Information****Protective Measures**

Use personal protective clothing and avoid contact with eyes and skin. Change soiled work clothes and wash hands before breaks and after finishing work. Take care for sufficient ventilation or exhaust on the workshop place.  
Local regulations as well as health and safety advice on packaging labels must be observed.

**Ecology****Transportation Class****Important Notes**

Residues of material must be removed according to local regulations. Fully cured material can be disposed of as household waste under agreement with the responsible local authorities.  
Detailed health and safety information as well as detailed precautionary measures e.g. physical, toxicological and ecological data can be obtained from the Material Safety Data Sheet.

**Toxicity**

## Legal Notes

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request or access on the Internet under [www.sika.co.za](http://www.sika.co.za).



Sika South Africa (Pty) Ltd  
9 Hocking Place,  
Westmead, 3608  
South Africa

E-Mail: [headoffice@za.sika.com](mailto:headoffice@za.sika.com)  
Phone +27 31 792 6500  
Telefax +27 31 700 1760  
[www.sika.co.za](http://www.sika.co.za)

