

## PRODUCT DATA SHEET

# Sikafloor®-262 AS N

Electrostatically conductive, smooth, two-part epoxy floor covering

### DESCRIPTION

Sikafloor®-262 AS N is a two-part, electrostatically conductive, self-smoothing, coloured epoxy resin coating with.

### USES

Sikafloor®-262 AS N may only be used by experienced professionals.

Sikafloor®-262 AS N is used as a:

- Smooth, electrostatically conductive floor covering

### CHARACTERISTICS / ADVANTAGES

- Electrostatically conductive
- Good resistance to specific chemicals
- Good mechanical resistance
- Easy to clean and maintain
- Impermeable to liquids

### ENVIRONMENTAL INFORMATION

- Contributes towards satisfying Indoor Environmental Quality (EQ) Credit: Low-Emitting Materials under LEED® v4 — 1–3 points
- Contributes towards satisfying Materials and Resources (MR) Credit: Building product disclosure and optimization — Environmental Product Declarations under LEED® v4 — 1 point

### PRODUCT INFORMATION

#### Chemical Base

Solvent-free epoxy

#### Packaging

Container Part A	21 kg
Container Part B	4.0 kg
Container Part A + Part B	25 kg ready to mix unit

Refer to the current price list for available packaging variations.

### APPROVALS / STANDARDS

- Coating Compatibility AA-P 128, Sikafloor®, Polymer Institut, Report No. P 5541
- Material testing PV 3.10.7, Sikafloor®-262 AS N, HQM, Report No. 14-04-14201871-
- Particle Test ISO 14644-1, Sikafloor®-262 AS N, CSM Fraunhofer, Certificate No.
- Outgassing emissions VDI 2083-17, Sikafloor®-262 AS N, CSM Fraunhofer, Certificate
- Biological Resistance ISO 846, Sikafloor®-262 AS N, No. SI 1412-740
- CE marking and declaration of performance based on EN 13813:2002 Screed material and floor screeds — Screed material — Properties and requirements — Synthetic resin screed material
- CE marking and declaration of performance based on EN 1504-2:2004 Products and systems for the protection and repair of concrete structures — Surface protection systems for concrete — Coating

<b>Shelf Life</b>	24 months from date of production		
<b>Storage Conditions</b>	The Product must be stored in original, unopened and undamaged sealed packaging in dry conditions at temperatures between +5 °C and +30 °C. Always refer to the packaging. Refer to the current Safety Data Sheet for information on safe handling and storage.		
<b>Density</b>	Mixed Product	1.53 kg/l unfilled	(EN ISO 2811-1)
	Part A	1.69 kg/l	
	Part B	1.03 kg/l	
<b>Solid content by weight</b>	97 %		
<b>Solid content by volume</b>	97 %		
<b>Colour</b>	Cured appearance	Semi gloss finish	

## TECHNICAL INFORMATION

<b>Abrasion Resistance</b>	< 3000 mg (H22 / 1000 cycles / 1000 g)		(EN ISO 5470-1)
<b>Compressive Strength</b>	Cured 28 days at +23 °C	80 N/mm <sup>2</sup> (tested as filled with 30 % quartz sand)	(EN ISO 604)
<b>Tensile Strength in Flexure</b>	Cured 28 days at +23 °C	40 N/mm <sup>2</sup> (filled with 30 % quartz sand)	(ISO 178)
<b>Tensile Adhesion Strength</b>	> 1.5 N/mm <sup>2</sup> (failure in concrete)		(EN 1542)
<b>Electrostatic Behaviour</b>	Resistance to ground	$R_G < 10^9 \Omega$	(IEC 61340-4-1)
	Typical average resistance to ground	$R_G < 10^5 - 10^6 \Omega$	
	Note: This product fulfils the requirements of ATEX 137. Note: Measurement results can be affected by ESD clothing, ambient conditions, measurement equipment, cleanliness of the floor and the test personnel.		

## APPLICATION INFORMATION

<b>Mixing Ratio</b>	Part A : Part B (by weight)		84 : 16
<b>Consumption</b>	<b>Coating system</b>	<b>Product</b>	<b>Consumption</b>
	Self-smoothing wearing course for high aesthetic demands (film thickness ~ 1.5 mm)	Sikafloor®-262 AS Nfilled with Sikafloor® Filler-1	Min. 2.25 kg binder + 0.25 kg Sikafloor® Filler-1. Max. 2.0 kg binder + 0.5 kg Sikafloor® Filler-1
	Self-smoothing wearing course (film thickness ~ 1.5 mm)	Sikafloor®-262 AS N filled with quartz sand F34	Min. 2.25 kg binder + 0.25 kg quartz sand F34 Max. 1.75 kg binder + 0.75 kg quartz sand F34

Note: Consumption data is theoretical and does not allow for any additional material due to surface porosity, surface profile, variations in level, wastage or any other variations. Apply the Product to a test area to calculate the exact consumption for the specific substrate conditions and proposed application equipment.

### Reduced conductivity due to excessive layer thickness

Note: Applying the Product in excess of the stated thickness will result in reduced conductivity.

<b>Product Temperature</b>	Maximum	+30 °C		
	Minimum	+10 °C		
<b>Ambient Air Temperature</b>	Maximum	+30 °C		
	Minimum	+10 °C		
<b>Relative Air Humidity</b>	Maximum	80 % r.h.		
<b>Dew Point</b>	Beware of condensation. The substrate and uncured applied product must be at least +3 °C above the dew point to reduce the risk of condensation or blooming on the surface of the applied product. Low temperatures and high humidity conditions increase the probability of blooming.			
<b>Substrate Temperature</b>	Maximum	+30 °C		
	Minimum	+10 °C		
<b>Substrate Moisture Content</b>	Please refer to the Product Data Sheet of the individual epoxy primer.			
<b>Pot Life</b>	+10 °C	40 minutes		
	+20 °C	25 minutes		
	+30 °C	15 minutes		
Note: Times are approximate and will be affected by changing ambient conditions, particularly temperature and relative humidity.				
<b>Applied Product Ready for Use</b>	<b>Temperature</b>	<b>Foot traffic</b>	<b>Light traffic</b>	<b>Full cure</b>
	+10 °C	30 hours	5 days	10 days
	+20 °C	24 hours	3 days	7 days
	+30 °C	16 hours	2 days	5 days
Note: Times are approximate and will be affected by changing ambient conditions, particularly temperature and relative humidity.				

## BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## FURTHER DOCUMENTS

Refer to the following method statements:

- Sika Method Statement — Evaluation and preparation of surfaces for flooring systems
- Sika Method Statement 8508410 Sikafloor® mixing and application

## LIMITATIONS

**IMPORTANT**

**Indentations in resin due to high temperature combined with high point loading**

Under certain conditions, underfloor heating or high ambient temperatures combined with high point loading may lead to indentations in the resin.

## ECOLOGY HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

## APPLICATION INSTRUCTIONS

### EQUIPMENT

Select the most appropriate equipment required for the project.

#### MIXING

- Electric single-paddle mixer (300 to 400 rpm)
- Electric double-paddle mixer (> 700 W, 300 rpm to 400 rpm)
- Scraper
- Clean mixing containers

#### APPLICATION

- Mixed material carrier
- Large-surface scraper no. 656, toothed blades no. 25 ([www.polyplan.com](http://www.polyplan.com))
- Steel spike rollers

### SUBSTRATE QUALITY

**IMPORTANT**

**Reduced service life due to incorrect treatment of cracks**

The incorrect assessment and treatment of cracks may lead to a reduced service life and reflective cracking.

1. For static cracks, ensure the width is suitable for overcoating with Sikafloor®-262 AS N.
2. For dynamic cracks, ensure the movement is within the movement capacity of Sikafloor®-262 AS N.

## TREATMENT OF JOINTS AND CRACKS

Construction joints and existing static surface cracks in substrate require pre-treating before full layer application. Use Sikadur® or Sikafloor® resins.

## SUBSTRATE CONDITION

Cementitious substrates must be structurally sound and of sufficient compressive strength (minimum 25 N/mm<sup>2</sup>) with a minimum tensile strength of 1.5 N/mm<sup>2</sup>.

Substrates must be clean, dry and free of contaminants such as dirt, oil, grease, coatings, laitance, surface treatments and loose friable material.

## SUBSTRATE PREPARATION

### IMPORTANT

#### Surface defects due to voids in the substrate

Voids and blow holes in the substrate will weaken the surface and damage the covering Product if not repaired during the preparation process.

1. Fully expose blow holes and voids during surface preparation to identify the required repairs.
  1. Remove weak cementitious substrates.
  2. Prepare cementitious substrates mechanically using abrasive blast cleaning, abrasive planing or scarifying equipment to remove cement laitance.
  3. Where thin layer resins are going to be applied, remove high spots by grinding.
  4. Remove all dust, loose and friable material from the application surface with industrial vacuuming equipment.
  5. Level the surface or fill cracks, blow holes and voids with products from the Sikafloor®, Sikadur® and Sikagard® range of materials.

#### Substrate levelling for conductive floors

Note: The concrete or screed substrate has to be primed or levelled in order to achieve an even surface. Unevenness influences the film thickness and thus the conductivity.

For additional information on products for levelling and repairing defects, contact Sika® Technical Services.

## SUBSTRATE PREPARATION OF NON-CEMENTITIOUS SUBSTRATES

For information on substrate preparation of non-cementitious substrates, contact Sika® Technical Services.

## MIXING

### FILLED MIXING PROCEDURE

1. Mix Part A (resin) until the coloured pigment is dispersed and a uniform colour is achieved.
2. Add Part B (hardener) to Part A.
3. While mixing Parts A + B, gradually add the required filler or aggregates.
4. **IMPORTANT** Do not mix excessively. Mix for a further 2 minutes until a uniform mix is achieved.
5. To ensure thorough mixing, pour materials into another container and mix again to achieve a smooth and uniform mix.
6. During the final mixing stage, scrape down the sides and bottom of the mixing container with a flat or straight edge trowel at least once to ensure complete mixing.

### UNFILLED MIXING PROCEDURE

1. Mix Part A (resin) until the coloured pigment is dispersed and a uniform colour is achieved.
2. Add Part B (hardener) to Part A.
3. **IMPORTANT** Do not mix excessively. Mix Part A + B continuously for ~3 minutes until a uniformly coloured mix is achieved.
4. **(Optional)** For vertical application, gradually add between 2.5 % and 4 % by weight of flooring resin of Sika® Extender T.
5. If additional materials were added, mix for a further 2 minutes until a uniform mix is achieved.
6. To ensure thorough mixing, pour materials into another container and mix again to achieve a smooth and uniform mix.
7. During the final mixing stage, scrape down the sides and bottom of the mixing container with a flat or straight edge trowel at least once to ensure complete mixing.

## APPLICATION

### IMPORTANT

#### Damaged finish due to heating with fossil fuel heaters

Fossil fuel heaters powered by gas, oil or paraffin produce large quantities of both carbon dioxide and water vapour, which may adversely affect the finish.

1. For temporary heating, use only electrically powered warm air blower systems. Do not use gas, oil, paraffin or other fossil fuel heaters.

### IMPORTANT

#### Apply approved reference area before full system application

Apply a reference area before the application of a full system. The reference area must be assessed and accepted by all parties before full project application.

### IMPORTANT

#### Protect from moisture

After application, protect the Product from damp, condensation and direct water contact for at least 24 hours.

#### Preconditions

**IMPORTANT** Do not blind the primer. The conductive priming coat has been applied and has dried tack-free all over.

1. Pour the mixed Product onto the surface. For the consumption, refer to Application Information.
2. Apply the Product evenly over the surface with a serrated trowel.
3. Turn the serrated trowel and smooth the surface for an aesthetically higher grade of finish.
4. **IMPORTANT** This process must happen within 10 minutes of application. Back roll the surface in two directions at right angles with a spike roller.

### IMPORTANT

#### Temporary moisture barrier required if substrate moisture exceeds 4 %

If the substrate moisture content measured with the CM-method is > 4 % by weight, apply a temporary moisture barrier consisting of Sikafloor® EpoCem®.

1. Contact Sika technical services for more information.

## CLEANING OF TOOLS

Clean all tools and application equipment with Sika® Thinner C immediately after use. Hardened material can only be removed mechanically.

## MAINTENANCE

To maintain the appearance of the floor after application:

1. Immediately remove all spillages.
2. **IMPORTANT** Use detergents and maintenance layer products in strict accordance with the Manufacturer's instructions. Regularly clean the floor using suitable detergents and maintenance layers using equipment such as rotary brushes, mechanical scrubbers, scrubber-dryers, high-pressure washers and wash and vacuum machines.

For further information refer to: Method statement Cleaning Regime Sikafloor® Floor Coverings

## LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

### Sika South Africa (Pty) Ltd

9 Hocking Place,  
Westmead, 3608  
South Africa  
Phone +27 31 792 6500  
www.sika.co.za



### Product Data Sheet

Sikafloor®-262 AS N  
June 2026, Version 05.01  
020811020020000002

Sikafloor-262ASN-en-ZA-(06-2026)-5-1.pdf