

PRODUCT DATA SHEET

Sikagard®-62

2-part epoxy protective coating

DESCRIPTION

Sikagard®-62 is a two part, rigid, 100% solids, coloured high build epoxy resin based protective coating.

USES

Sikagard®-62 may only be used by experienced professionals.

- Chemical resistant protective layer on concrete, stone, cementitious mortars and renderings, epoxy cement, epoxy resin based products and steel
- Lining in storage tanks and silos
- Anti-corrosion coating on steel in food processing plants, sewage works, farms, agricultural enterprises, chemical and pharmaceutical facilities and beverage industry

CHARACTERISTICS / ADVANTAGES

- Solvent free
- Good mechanical and chemical resistance
- High build
- Impervious to liquids
- Easy to mix and to apply

ENVIRONMENTAL INFORMATION

According USGBC LEED Rating Sikagard®-62 conforms to the requirements of LEED EQ Credit 4.2: Low –Emitting Materials: Paints & Coatings SCAQMD Method 304-91, VOC Content < 100g/l

APPROVALS / STANDARDS

- Coating for concrete protection according the requirements of EN 1504-2:2004, Declaration of Performance 0206060100100000011008, certified by FPC Notified Body and provided with CE marking
- WRAS, test report No. M104991, 2011, Contact with water for wholesome purposes according BS 6920-1:2000

PRODUCT INFORMATION

| Chemical Base | Epoxy resin | |
|---------------------|-------------------------|--|
| Packaging | Part A | 3.75ltr or 5.25 kg Containers |
| | Part B | 1.25ltr or 1.3 kg Containers |
| Appearance / Colour | RAL 7032 (pebble grey |), other on request |
| Shelf Life | Part A: 12 months | |
| | Part B: 12 months | |
| | From date of production | on if stored properly. |
| Storage Conditions | | stored properly in original, unopend and undam, in dry conditions at temperatures between +5°C |

Product Data Sheet

Sikagard®-62 September 2020, Version 04.03 020606010010000001

| Density | Part A Part B | approx. 1.40 kg/l approx. 1.035 kg/l | (EN ISO 2811-1) |
|-------------------|--|---|-----------------|
| | Mixed resin approx Density values det | | |
| Solid Content | ~ 100 % | | |
| TECHNICAL INFORMA | ATION | | |
| Shore D Hardness | approx. 80 | | (DIN 5305) |
| | | | |

| Shore D Hardness | approx. 80 | | | (DIN 5305) |
|---------------------------|---|----------------------|------------|---------------|
| Mechanical Resistance | Taber Abraser | CS 10/ 1000/ 1000 | 24.4mg | (ASTM D 4060) |
| | Taber Abraser | CS 17/ 1000/ 1000 | 70 mg | |
| | Taber Abraser | H 22/ 1000/ 1000 | 560.6mg | |
| Tensile Adhesion Strength | > 1.5 N/mm² to conrete | | (ISO 4624) | |
| Chemical Resistance | Please contact Sika technical service for specific information. | | nation. | |

| Circinical Resistance | rease contact six teermear service for specific information. | | |
|-----------------------|--|----------|--|
| Thermal Resistance | Exposure | Dry heat | |
| | Permanent | +50°C | |
| | max. 7 days | +80°C | |
| | max. 12 hours | +100°C | |
| | | · ' | |

APPLICATION INFORMATION

| Mixing Ratio | Part A: Part B = 3:1 by weight | | | |
|----------------------------|---|------------|--------------|-----------|
| Consumption | approx. 0.30 kg/m² (0.2L/m²) per layer | | | |
| Layer Thickness | approx. 0.2 mm per layer | | | |
| Ambient Air Temperature | +8 °C - +40 °C | | | |
| Relative Air Humidity | < 80 % | | | |
| Substrate Temperature | +8 °C − +4 0°C ≥3 °C above dew point, beware of condensation | | | |
| Pot Life | Temperature | | Time | |
| | +10 °C | | approx. 30 m | in |
| | +20 °C | | approx. 20 m | in |
| | +30 °C | | approx. 10 m | in |
| Waiting Time / Overcoating | Temperature | Min. | Max. | Full cure |
| | +10°C | ~ 30 hours | ~ 3 days | ~ 14 days |
| | . 20%C | ~ 10 hours | ~ 2 days | ~ 10days |
| | +20°C | 10 110013 | z uays | Tuuays |

APPLICATION INSTRUCTIONS

Prior to mixing stir part A mechanically. When all of part B has been added to part A mix continuously for 3 minutes until an uniform mixed has been achieved. Use a low speed electrical stirrer (300-400 rpm) to avoid air entrapment. To ensure proper mixing pour material into a clean container and stir again. Apply by brush, roller or airless spray.

CLEANING OF TOOLS

Clean all tools with Thinner C immediately after use. Hardened and/or cured material can only be removed mechanically.

LIMITATIONS

This product may only be used by experienced professionals. Do not apply Sikagard®-62 on moist substrates

Product Data Sheet Sikagard®-62

September 2020, Version 04.03 020606010010000001



Sag resistance on vertical surface is approx. 200µm. Freshly applied Sikagard®-62 must be protected from damp, condensation and water for at least 24 hours For exact colour matching ensure the use f the same control batch numbers.

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

ECOLOGY HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

DIRECTIVE 2004/42/CE - LIMITATION OF EMISSIONS OF VOC

According to the EU-Directive 2004/42, the maximum allowed content of VOC (Product category IIA / j type sb) is 550 / 500 g/l (Limits 2007 / 2010) for the ready to use product. The maximum content of Sikagard®-62 is < 500 g/l VOC for the ready to use product.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request. It may be necessary to adapt the above disclaimer to specific local laws and regulations. Any changes to this disclaimer may only be implemented with permission of Sika® Corporate Legal in Baar.

Sika South Africa (Pty) Ltd

9 Hocking Place, Westmead, 3608 South Africa Phone +27 31 792 6500 www.sika.co.za







Product Data Sheet
Sikagard®-62
September 2020, Version 04.03
020606010010000001



Sikagard-62-en-ZA-(09-2020)-4-3.pdf