

## PRODUCT DATA SHEET

# Sika BlackSeal® Lastic

Rubberised bituminous waterproofing coating

## DESCRIPTION

Sika BlackSeal® Lastic is a rubberised bitumen emulsion coating, which is used as a stand alone coating or in conjunction with Sika BlackSeal membrane (polyprop fabric) to form a waterproofing system.

## USES

Waterproofing for various applications such as:

- Flat roof waterproofing
- Waterproofing of water retaining structures
- Flashing of roofs
- Gutters
- Parapet walls
- Sealing of fixings, lap joints and roof screws

## CHARACTERISTICS / ADVANTAGES

- Applied by with brush, roller or trowel
- Supplied ready to use
- No primer needed
- Easily applied
- Non-sag on vertical surfaces
- Remains flexible at low temperature
- Crack-bridging
- Non-toxic

## PRODUCT INFORMATION

<b>Chemical Base</b>	Emulsion containing bitumen mastic
<b>Packaging</b>	5ltr and 20ltr containers
<b>Colour</b>	Pasty black
<b>Shelf Life</b>	12 months
<b>Storage Conditions</b>	Store in closed,sealed and undamaged packaging in dry conditions at temperatures between +5°C and +30°C. Protect from direct sunlight.
<b>Density</b>	~1.02kg/l
<b>Solid content by volume</b>	~47% by Vol.

<b>Service Temperature</b>	-30°C to 70°C dry
<b>Layer Thickness</b>	2mm max.
<b>Ambient Air Temperature</b>	+10°C min. / +35°C max
<b>Substrate Temperature</b>	+10°C min. / +35°C max
<b>Substrate Moisture Content</b>	<3%
<b>Curing Time</b>	Surface - dry after 3 hours at 23°C Dependant on ambient temperature, substrate temperature, relative humidity and the thickness of the coating

## BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## LIMITATIONS

Do not use this product for waterproofing against hydrostatic pressure.

Do not apply the product during rain.

Protect newly applied material from rain, etc. until hardened.

Warm the product before use in cold weather.

Before attempting to waterproof a Koi pond please contact the Technical Department of Sika for detailed instructions.

## ECOLOGY HEALTH AND SAFETY

## APPLICATION INSTRUCTIONS

### SUBSTRATE QUALITY

Substrate must be smooth, dry, free of dust, oil or grease and loose or friable particles. Surface defects including blowholes, voids, honeycombing, etc., in the concrete must be repaired with suitable Sika mortars before coating.

### SUBSTRATE PREPARATION

Rinse concrete surfaces with clean water.

Clean contaminated substrates by suitable means including steam cleaning, high pressure water jetting, etc.

#### Concrete substrate:

Prime substrates with one part Sika® Blackseal Lastic diluted by one part water.

#### Metal surfaces:

After degreasing surface prime new galvanised surfaces with Sika® Blackseal Primer.

Old surfaces which have been effected by rust should be thoroughly cleaned and primed with a good metal etch primer.

## APPLICATION METHOD / TOOLS

**Manual application:** Apply with a suitable brush or roller.

**First coat:** Brush on a thick coat of Sika BlackSeal® Lastic onto the primed surface at a spread rate of 1,25m<sup>2</sup>/litre. Embed the membrane into the wet coat, ensuring that the bitumen impregnates the membrane and all air is expelled.

**Second coat:** A second coat is applied once the first coat has dried sufficiently (approx. 3hours), at a spread rate of 2,0m<sup>2</sup>/litre. The membrane must be well saturated to ensure a good watertight barrier is formed.

**Final coat:** A final coat should be applied once the second coat has dried. This coat should be applied at the rate of 1,25m<sup>2</sup>/litre to finish off the system. The completed waterproofing system should be left for approximately 2 weeks before filling a water retaining structure with water. Ambient temperatures have an effect on the time period required for full cure. If unsure please contact the Technical Department of Sika, before doing so.

## LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request. It may be necessary to adapt the above disclaimer to specific local laws and regulations. Any changes to this disclaimer may only be implemented with permission of Sika® Corporate Legal in Baar.

### Sika South Africa (Pty) Ltd

9 Hocking Place,  
Westmead, 3608  
South Africa  
Phone +27 31 792 6500  
[www.sika.co.za](http://www.sika.co.za)



### Product Data Sheet

Sika BlackSeal® Lastic  
May 2021, Version 01.04  
020706301000000108

SikaBlackSealLastic-en-ZA-(05-2021)-1-4.pdf