

PRODUCT DATA SHEET

SikaPlast® PH 3841

(formerly MasterPolyheed® 3841)

Water reducing superplasticizer for the production of high quality day-to-day ready-mix concrete

DESCRIPTION

SikaPlast® PH 3841 is an economical admixture based on modified polycarboxylic ether. The product has been primarily developed for applications in ready mix and site-batched concrete.

SikaPlast® PH 3841 is specially designed to allow for mid to high range mix water reduction while maintaining flexible degrees of slump retention without retardation.

SikaPlast® PH 3841 is free of chloride & low alkali. It is compatible with all types of cements.

SikaPlast® PH 3841 admixture provides the concrete producer with the ability to immediately create the optimal admixture system for changing and fluctuating regional raw materials, environmental conditions and project requirements.

SikaPlast® PH 3841 admixture gives the concrete producer the ability to consistently produce and deliver quality day-to-day concrete.

USES

- Ready mixed concrete
- Pumped concrete
- High workability concrete without segregation or bleeding.
- Improved durability concrete.
- Congested/complex reinforced sections.
- Concrete mixes utilizing supplementary cementitious materials.

CHARACTERISTICS / ADVANTAGES

- Good dispersion even in mixes with high fines
- Improved workability for longer periods
- Lower pumping pressure
- Resistance to segregation even at greater workability
- Good mid-range slump retention
- Reduced water content for a given workability.
- Easier pumpability and place ability.
- Higher ultimate strengths
- Greater ease in finishing concrete

PRODUCT INFORMATION

Packaging	SikaPlast® PH 3841 is available in 1000 litre IBC's.
Shelf Life	The shelf life is 12 months when stored correctly.
Storage Conditions	SikaPlast® PH 3841 should be stored out of direct sunlight and protected from extremes of temperature.
Appearance / Colour	Brownish Liquid
Density	1.085 - 1.120
pH-Value	6.5 – 9.5
Total Chloride Ion Content	“chloride-free” to EN 934-2

APPLICATION INFORMATION

Recommended Dosage	The normally recommended dosage rate of SikaPlast® PH 3841 is: 0.4 to 1.2 litre per 100kg of total cementitious material. Other dosages may be recommended in special cases according to the specific site conditions. In this case, please consult our Technical Services Department for advice.
Dispensing	SikaPlast® PH 3841 is a ready-to-use admixture to be added to the concrete as a separate component. Optimal result is obtained if SikaPlast® PH 3841 is poured into the concrete mix right after the addition of the first 80% of the mixing water, i.e., when all solids are wetted. Avoid adding the admixture to the dry aggregates.
Consumption	SikaPlast® PH 3841 is not compatible with Sikament RB superplasticizers. SikaPlast® PH 3841 is suitable for mixes containing: <ul style="list-style-type: none">• Microsilica (Silica Fume)• Fly Ash (PFA)• GGBS (ground granulated blast furnace slag)

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

FURTHER DOCUMENTS

No special requirements must be observed during use. Protection gloves and glasses are however recommended. SikaPlast® PH 3841 is non-flammable, non-toxic or irritant and is not subject to special transport requirements.

SikaPlast® PH 3841 contains no hazardous substances requiring labelling. For further information refer to the Material Safety Data Sheet.

LIMITATIONS

The occurrence of a surface layer with SikaPlast® PH 3841 is normal and will have no effect on the performance of the product.

ECOLOGY HEALTH AND SAFETY

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request. It may be necessary to adapt the above disclaimer to specific local laws and regulations. Any changes to this disclaimer may only be implemented with permission of Sika® Corporate Legal in Baar.

Sika South Africa (Pty) Ltd
9 Hocking Place,
Westmead, 3608
South Africa
Phone +27 31 792 6500
www.sika.co.za



Product Data Sheet
SikaPlast® PH 3841
September 2023, Version 01.01
02130100000002087

SikaPlastPH3841-en-ZA-(09-2023)-1-1.pdf