

Product Data Sheet
Edition 06/08/2012
Identification no:
02 08 01 04 012 0 000001
Sikafloor®-356 N

Sikafloor®-356 N

2-part PUR transparent matt seal coat

Product Description

Sikafloor®-356 N is a two part, tough elastic, transparent, solvent containing, polyurethane matt finish seal coat.

Uses

- Matt sealer for Sikafloor® smooth epoxy coatings
- Matt finish for Sikafloor® broadcast and sealed screeds in dry processing areas

Characteristics / Advantages

- Tough-elastic
- Good mechanical and chemical resistance
- Non-yellowing
- Easy application

Product Data

Form

Appearance / Colours

Resin - part A: transparent, liquid
Hardener - part B: transparent, liquid

Packaging

Part A: 8.0 kg
Part B: 2.0 kg
Part A+B: 10 kg unipacks

Storage Conditions / Shelf Life

6 months from date of production if stored properly in original, unopened and undamaged sealed packaging in dry conditions at temperatures between +5°C and +30°C.

Technical Data

Chemical Base

PUR

Density

Part A: ~ 1.13 kg/l
Part B: ~ 0.89 kg/l
Mixed Resin: ~ 0.97 kg/l

(DIN EN ISO 2811-1)

All Density values at +23°C

System Information

System Structure

Seal coat of smooth EP coatings:
 Base coat: Sikafloor®-263 SL / 264
 Matt seal coat: 1 x Sikafloor®-356 N

Matt finish for sealed broadcast coatings in dry processing areas:
 Base coat: e.g. Sikafloor®-263 SL / 264 + quartz sand
 Seal coat: 1-2 x Sikafloor®-263 SL / 264
 Matt seal coat: 1 x Sikafloor®-356 N

Application Details

Consumption / Dosage

Coating System	Product	Consumption
Seal coat for smooth coatings	Sikafloor®-356 N	0.10 - 0.15 kg/m ²
Finishing of sealed broadcast coatings	Sikafloor®-356 N	0.15 - 0.30 kg/m ²

These figures are theoretical and do not allow for any additional material due to surface porosity, surface profile, variations in level or wastage etc.

Substrate Quality

The substrate must be clean, dry and free of all contaminants such as dirt, oil, grease, coatings and surface treatments, etc.

If in doubt, apply a test area first.

Substrate Preparation

All dust, loose and friable material must be completely removed from all surfaces before application of the product, preferably by brush and/or vacuum.

Application Conditions / Limitations

Substrate Temperature +10°C min. / +30 C max.

Ambient Temperature +10°C min. / +30 C max.

Relative Air Humidity 80% r.h. max.

Dew Point Beware of condensation!

The substrate and uncured floor must be at least 3°C above dew point to reduce the risk of condensation or blooming on the floor finish.



Application Instructions

Mixing	Part A : part B = 80 : 20 (by weight)														
Mixing Time	<p>Prior to mixing, stir part A mechanically. When all of part B has been added to part A, mix continuously for 3 minutes until a uniform mix has been achieved.</p> <p>To ensure thorough mixing pour materials into another container and mix again to achieve a consistent mix.</p> <p>Over mixing must be avoided to minimise air entrainment.</p>														
Mixing Tools	Sikafloor®-356 N must be thoroughly mixed using a low speed electric stirrer (300 - 400 rpm) or other suitable equipment.														
Application Method / Tools	<p>Prior to application, confirm r.h. and dew point.</p> <p><i>Seal coat / matt finish:</i> Uniformly spread Sikafloor®-356 N using a short pile nylon roller.</p> <p>A seamless finish can be achieved if a “wet” edge is maintained during application.</p>														
Cleaning of Tools	Clean all tools with Thinner C immediately after use. Hardened and/or cured material can only be removed mechanically.														
Potlife	<table><tr><th>Temperature</th><th>Time</th></tr><tr><td>+10°C</td><td>~ 120 minutes</td></tr><tr><td>+20°C</td><td>~ 60 minutes</td></tr><tr><td>+30°C</td><td>~ 20 minutes</td></tr></table>			Temperature	Time	+10°C	~ 120 minutes	+20°C	~ 60 minutes	+30°C	~ 20 minutes				
Temperature	Time														
+10°C	~ 120 minutes														
+20°C	~ 60 minutes														
+30°C	~ 20 minutes														
Waiting Time / Overcoating	<p>Before applying Sikafloor®-356 N on Sikafloor®-263 SL / 264 allow:</p> <table><tr><th>Substrate temperature</th><th>Minimum</th><th>Maximum</th></tr><tr><td>+10°C</td><td>48 hours</td><td>4 days</td></tr><tr><td>+20°C</td><td>24 hours</td><td>3 days</td></tr><tr><td>+30°C</td><td>18 hours</td><td>2 days</td></tr></table> <p>Times are approximate and will be affected by changing ambient conditions particularly temperature and relative humidity.</p>			Substrate temperature	Minimum	Maximum	+10°C	48 hours	4 days	+20°C	24 hours	3 days	+30°C	18 hours	2 days
Substrate temperature	Minimum	Maximum													
+10°C	48 hours	4 days													
+20°C	24 hours	3 days													
+30°C	18 hours	2 days													
Notes on Application / Limitations	<p>Freshly applied Sikafloor®-356 N must be protected from damp, condensation and water for at least 24 hours.</p> <p>Uncured material reacts in contact with water (foaming). During application care must be taken that no sweat drops into fresh Sikafloor®-356 N (wear head and wrist bands)</p> <p>Apply Sikafloor®-356 N to tack free Sikafloor®-263 SL / 264</p> <p>Unevenness of the substrate and inclusions of dirt cannot be covered by thin sealer coats. Therefore the substrate and adjacent areas must be cleaned thoroughly prior to application.</p> <p>If heating is required do not use gas, oil, paraffin or other fossil fuel heaters, these produce large quantities of both CO₂ and H₂O water vapour, which may adversely affect the finish. For heating use only electric powered warm air blower systems.</p>														



Curing Details

Applied Product ready for use

Temperature	Foot traffic	Light traffic	Full cure
+10°C	~ 36 hours	~ 5 days	~ 10 days
+20°C	~ 24 hours	~ 3 days	~ 7 days
+30°C	~ 16 hours	~ 2 days	~ 3 days

Note: Times are approximate and will be affected by changing ambient conditions

Cleaning / Maintenance

Methods

To maintain the appearance of the floor after application, Sikafloor®-356 N must have all spillages removed immediately and be regularly cleaned using rotary brush, mechanical scrubbers, scrubber dryer, high pressure washer, wash and vacuum techniques etc using suitable detergents and waxes.

Value Base

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

Local Restrictions

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

Health and Safety Information

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.

Legal Notes

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.



Sika South Africa (Pty) Ltd
9 Hocking Place,
Westmead, 3608
South Africa

E-mail: headoffice@za.sika.com
Phone +27 31 792 6500
Telefax +27 31 700 1760
www.sika.co.za

