

Product Data Sheet
Edition 29/06/2016
Identification no:
02 03 02 02 003 0 000001
Sikadur®-32 Normal

Sikadur®-32 Normal

2-part structural epoxy bonding agent

Product Description

Sikadur®-32 Normal is a moisture tolerant, structural, two part bonding agent, based on a combination of epoxy resins and special fillers, designed for use at temperatures between +10°C and +30°C.

Uses

As a structural bonding agent and adhesive for:

- Concrete elements (including bonding fresh to hardened concrete)
- Hard natural stone
- Ceramics, fibre-cement
- Mortar, Bricks, Masonry
- Steel, Iron, Aluminium
- Wood
- Polyester / fibreglass and Epoxy resin materials
- Glass

Characteristics / Advantages

Sikadur®-32 Normal has the following advantages:

- Easy to mix and apply
- Suitable for dry and damp concrete surfaces
- Very good adhesion to most construction materials
- High Bond Strength
- Hardens without shrinkage
- Different coloured components (for mixing control)
- No primer needed
- High initial and ultimate mechanical strength
- Impermeable to liquids and water vapour
- Good chemical resistance

Construction



Mechanical / Physical Properties

Compressive Strength*

(According to ASTM D 695-95)

| Curing time | Curing temperature | | |
|-------------|-----------------------|-----------------------|-----------------------|
| | +10°C | +23°C | +30°C |
| 1 day | - | ~24 N/mm ² | ~30 N/mm ² |
| 3 days | ~13 N/mm ² | ~28 N/mm ² | ~41 N/mm ² |
| 7 days | ~32 N/mm ² | ~39 N/mm ² | ~52 N/mm ² |
| 14 days | ~42 N/mm ² | ~49 N/mm ² | ~56 N/mm ² |

*at 4% elongation

Flexural Strength

(According to DIN EN 53452)

| Curing time | Curing temperature | | |
|-------------|-----------------------|-----------------------|-----------------------|
| | +10°C | +23°C | +30°C |
| 1 day | - | ~29 N/mm ² | ~52 N/mm ² |
| 3 days | ~12 N/mm ² | ~48 N/mm ² | ~57 N/mm ² |
| 7 days | ~24 N/mm ² | ~50 N/mm ² | ~60 N/mm ² |
| 14 days | ~42 N/mm ² | ~56 N/mm ² | ~65 N/mm ² |

Tensile Strength

(According to ISO 527)

| Curing time | Curing temperature | | |
|-------------|-----------------------|-----------------------|-----------------------|
| | +10°C | +23°C | +30°C |
| 1 day | - | ~16 N/mm ² | ~24 N/mm ² |
| 3 days | - | ~25 N/mm ² | ~30 N/mm ² |
| 7 days | ~20 N/mm ² | ~32 N/mm ² | ~33 N/mm ² |
| 14 days | ~25 N/mm ² | ~33 N/mm ² | ~34 N/mm ² |

Bond Strength

(According to EN ISO 4624, EN 1542 and EN 12188)

| Time | Temperature | Substrate | Bond strength |
|--------|-------------|----------------|---------------------------|
| 7 days | +10°C | Concrete dry | > 3 N/mm ² * |
| 7 days | +10°C | Concrete moist | > 3 N/mm ² * |
| 1 day | +10°C | Steel | 6 - 10 N/mm ² |
| 3 days | +10°C | Steel | 10 - 14 N/mm ² |
| 3 days | +23°C | Steel | 11 - 15 N/mm ² |
| 3 days | +30°C | Steel | 13 - 17 N/mm ² |

*100% concrete failure.

E-Modulus

Tensile:

~ 4'000 N/mm² (14 days at +23°C)

(According to ISO 527)

Flexural:

~ 3'600 N/mm² (14 days at +23°C)

(According to DIN EN 53452)

Compressive:

~ 3'250 N/mm² (14 days at +23°C)

(According to ASTM D695-95)

Elongation at Break

1.0 ± 0.1% (14 days at +23°C)

(According to ISO 527)

System Information

Application Details

Consumption / Dosage The consumption of Sikadur®-32 Normal is ~ 0.9 – 1.0 ltr/m² per mm of thickness.

Substrate Quality Hardened mortar and concrete must be older than 28 days (depending on any minimal strength requirements).
Verify the substrate strength by testing (concrete, masonry, natural stone).
The substrate surface (all types) must be clean, dry and free from contaminants such as dirt, oil, grease, existing surface treatments and coatings etc.
Steel substrates must be de-rusted to a condition similar to Sa 2.5.
The substrate must be sound and all loose or friable particles must be removed.

Substrate Preparation Concrete, mortar, stone and brick substrates.:
Concrete and other hardened mineral substrates must be prepared by suitable means such as high pressure water jetting and / or blastcleaning, in order to obtain surfaces that are sound, clean, dry and free from any cement laitance, ice, standing water, grease, oils, old coatings or other surface treatments. Any loose or friable particles must also be removed to achieve a contaminant free and open textured surface.
Steel substrates:
Steel surfaces must be cleaned and prepared thoroughly to the acceptable quality standard equivalent to Sa 2.5 i.e. normally by blastcleaning and then removing any dust by vacuum. Avoid dew point conditions.

Application Conditions / Limitations

Substrate Temperature +10°C min. / +30°C max.

Ambient Temperature +10°C min. / +30°C max.

Material Temperature Sikadur®-32 Normal must be applied at temperatures between +10°C and +30°C

Substrate Moisture Content Can be applied to mat damp concrete. In these situations apply by brush and work the material well into the substrate.

Dew Point Beware of condensation and dew point conditions!
Substrate temperature during application must be at least 3°C above dew point.

Application Instructions

Mixing Part A : part B = 2 : 1 by weight or volume

Mixing Time



Pre batched units:
Mix parts A+B together for at least 3 minutes with a mixing spindle attached to a slow speed electric drill (max. 300 rpm) until the material becomes smooth in consistency and a uniform grey colour. Avoid aeration while mixing. Then, pour the whole mix into a clean container and stir again for approx. 1 more minute at low speed to keep air entrapment at a minimum. Mix only that quantity which can be used within its potlife.

Application Method / Tools

Apply the mixed Sikadur®-32 Normal to the prepared surface by brush, roller, spray or with a trowel, and ensure uniform and complete coverage. On hardened concrete substrates mechanically prepared to receive fresh concrete, always apply by brush and work the material well into the substrate.

Place the fresh concrete whilst the Sikadur®-32 Normal layer is still 'tacky'. If the material becomes glossy and loses tackiness, apply a fresh coat with additional Sikadur®-32 Normal and proceed.

| | | | |
|---|--|--------------|----------------------------|
| Cleaning of Tools | Clean all tools and application equipment with Sika® Colma Cleaner immediately after use. Hardened / cured material can only be mechanically removed. | | |
| Pot-life | Pot-life (200 g) | | (According to EN ISO 9514) |
| | +10°C | +23°C | +30°C |
| | ~ 145 minutes | ~ 55 minutes | ~ 35 minutes |
| | The pot-life begins when the resin and hardener are mixed. It is shorter at high temperatures and longer at low temperatures. The greater the quantity mixed, the shorter the pot-life. To obtain longer workability at high temperatures, the mixed Sikadur®-32 Normal may be divided into portions. Another method is to chill parts A+B before mixing them (not below +5°C). | | |
| Notes on Application / Limitations | Sikadur® resins are formulated to have low creep under permanent loading. However due to the creep behaviour of all polymer materials under load, the long term structural design load must account for creep. Generally the long term structural design load must be lower than 20-25% of the failure load. Please consult a structural engineer for load calculations for your specific application. | | |
| Value Base | All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control. | | |
| Local Restrictions | Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields. | | |
| Health and Safety Information | For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data. | | |
| Legal Notes | The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request. | | |



Sika South Africa (Pty) Ltd
 9 Hocking Place,
 Westmead, 3608
 South Africa

E-mail: headoffice@za.sika.com
 Phone +27 31 792 6500
 Telefax +27 31 700 1760
www.sika.co.za

