

Sikalastic®-841 ST

Liquid applied pure polyurea membrane

Product Description

Sikalastic®-841 ST is a two part, elastic, 100% solids, very fast curing pure polyurea liquid applied membrane with very good chemical resistance.
Sikalastic®-841 ST shall not be used in closed structures containing biogenic sulphuric acid
Sikalastic®-841 ST can only be spray applied with special two part hot spray equipment.

Uses

- For waterproofing applications and anticorrosion applications on concrete and many other substrates:
Typical uses:
- Protective coatings
- Tank coatings/linings
- Bridge coatings
- Roof coatings
- Walkways and balconies
- Flooring and parking decks
- Industrial and manufacturing facilities
- Landscape and water containment
- Power plants
- Sewage and Waste Water Treatment plants
- Truck bed lining

Characteristics / Advantages

- Very fast reactivity and curing time
- Almost immediate return-to-service time
- Applicable in temperatures from -15°C to 70°C
- Performs in constant dry temperatures from -30°C to 100°C
- 100% solids with zero VOC
- Excellent crack-bridging properties
- Good chemical resistance
- Low yellowing
- Good abrasion resistance

Product Data

Form

Appearance / Colours

ISO - Part A: clear liquid
Resin - Part B: amber or grey liquid
Grey ~ RAL 7005 or un-pigmented (yellowish)



Packaging	Part A (net): 212 kg drum (189 liter) Part B (net): 191 kg drum (189 liter)																		
Storage																			
Storage Conditions / Shelf Life	Part A: 18 months Part B: 18 months From date of production if stored properly in original, unopened and undamaged sealed packaging in dry conditions at temperatures between +5°C and +30°C.																		
Technical Data																			
Chemical Base	Pure Polyurea																		
Density	Part A: ~ 1.12 kg/litre Part B: ~ 1.01 kg/litre All Density values at +23°C																		
Gel Time	6 to 20 seconds																		
Tack Free Time	60 to 120 seconds																		
Post Cure Time	24 hours																		
Solid Content	> 99%																		
Viscosity	Part A: ~ 720 to 880 mPas Part B: ~ 315 to 385 mPas																		
Mechanical / Physical Properties																			
Tensile Strength	> 15 N/mm ² DIN 53504																		
Shore D Hardness	~ 45 to 50 DIN 53505																		
Elongation at Break	375 to 425 % DIN 53504																		
Abrasion Resistance	< 15 mg (CS 17/1000/1000) EN ISO 5470-1 ~ 100 mg (H22/1000/1000)																		
Crackbridging properties	Static: > 2500µm at +23°C, class A5 DIN EN 1062-7 Dynamic: class B4.2 at -20°C																		
Resistance																			
Chemical Resistance	Sikalastic®-841 ST is resistant to many chemicals. Please ask for a detailed chemical resistance table.																		
Thermal Resistance	Sikalastic®-841 ST performs in constant temperatures from -30°C to 100°C.																		
Application Details																			
Consumption / Dosage	<table><tr><th>Coating System</th><th>Product</th><th>Consumption</th></tr><tr><td rowspan="2">System for concrete structures</td><td>1-2 x Sikafloor®-156 ZA or Sikafloor®-161, lightly broadcast with quartz sand, 0.3 - 0.8 mm (optional)</td><td>0.3 - 0.5 kg/m² per layer 1.0 - 1.5 kg/m²</td></tr><tr><td>1 x Sikalastic®-841 ST</td><td>~ 1.08 kg/m²/mm</td></tr><tr><td rowspan="2"></td><td>1-2 x Sika® Concrete Primer, Lightly broadcast with quartz sand, 0.3 - 0.8 mm (optional)</td><td>0.2 - 0.4 kg/m² per layer 1.0 - 1.5 kg/m²</td></tr><tr><td>1 x Sikalastic®-841 ST</td><td>~ 1.08 kg/m²/mm</td></tr><tr><td rowspan="2">System on carbon steel</td><td>2 x SikaCor® EG 1</td><td>~ 0.22 kg/m² per layer</td></tr><tr><td>1 x Sikalastic®-841 ST</td><td>~ 1.08 kg/m²/mm</td></tr></table> <p>These figures are theoretical and do not allow for any additional material due to surface porosity, surface profile, variations in level and wastage etc.</p>	Coating System	Product	Consumption	System for concrete structures	1-2 x Sikafloor®-156 ZA or Sikafloor®-161, lightly broadcast with quartz sand, 0.3 - 0.8 mm (optional)	0.3 - 0.5 kg/m² per layer 1.0 - 1.5 kg/m²	1 x Sikalastic®-841 ST	~ 1.08 kg/m²/mm		1-2 x Sika® Concrete Primer, Lightly broadcast with quartz sand, 0.3 - 0.8 mm (optional)	0.2 - 0.4 kg/m² per layer 1.0 - 1.5 kg/m²	1 x Sikalastic®-841 ST	~ 1.08 kg/m²/mm	System on carbon steel	2 x SikaCor® EG 1	~ 0.22 kg/m² per layer	1 x Sikalastic®-841 ST	~ 1.08 kg/m²/mm
Coating System	Product	Consumption																	
System for concrete structures	1-2 x Sikafloor®-156 ZA or Sikafloor®-161, lightly broadcast with quartz sand, 0.3 - 0.8 mm (optional)	0.3 - 0.5 kg/m² per layer 1.0 - 1.5 kg/m²																	
	1 x Sikalastic®-841 ST	~ 1.08 kg/m²/mm																	
	1-2 x Sika® Concrete Primer, Lightly broadcast with quartz sand, 0.3 - 0.8 mm (optional)	0.2 - 0.4 kg/m² per layer 1.0 - 1.5 kg/m²																	
	1 x Sikalastic®-841 ST	~ 1.08 kg/m²/mm																	
System on carbon steel	2 x SikaCor® EG 1	~ 0.22 kg/m² per layer																	
	1 x Sikalastic®-841 ST	~ 1.08 kg/m²/mm																	

Substrate Quality	<p>The concrete substrate must be sound and of sufficient compressive strength (minimum 25 N/mm²) with a minimum pull off strength of 1.5 N/mm².</p> <p>The substrate must be clean, dry and free of all contaminants such as dirt, oil, grease, coatings and surface treatments, etc.</p> <p>If in doubt, apply a test area first.</p>
Substrate Preparation	<p>Concrete substrates must be prepared mechanically using abrasive blast cleaning or scarifying equipment to remove cement laitance and achieve an open textured surface.</p> <p>Weak concrete must be removed and surface defects such as blowholes and voids must be fully exposed.</p> <p>Repairs to the substrate, filling of blowholes/voids and surface levelling must be carried out using appropriate products from the Sikafloor®, SikaDur® and SikaGard® range of materials.</p> <p>The concrete or screed substrate has to be primed or levelled in order to achieve an even surface.</p> <p>High spots must be removed by e.g. grinding.</p> <p>All dust, loose and friable material must be completely removed from all surfaces before application of the product, preferably by brush and/or vacuum.</p> <p>Steel surfaces must be prepared by blast cleaning to Sa 2 ½ (ISO 8501-1) or SSPC-SP 10. All weld splatter has to be removed joints and welds must be grinded in accordance with EN 14879-1. An average surface profile R_z ≥ 50µm must be achieved, the substrate has to be free from contaminants detrimental to adhesion, preferably by high pressure water jetting prior of blast cleaning.</p>
Application Conditions / Limitations	
Substrate Temperature	-15°C min. / +40°C max.
Ambient Temperature	-15°C min. / +40°C max.
Relative Air Humidity	85% RH max.
Substrate Moisture Content	<p>Primer Sikafloor® 156ZA and Sika® Concrete Primer ≤ 4% pbw moisture content. Test method: Sika®-Tramex meter, CM - measurement or Oven-dry-method. No rising moisture according to ASTM (Polyethylene-sheet)</p> <p>Primer Sikafloor® 161 ≤ 6% pbw moisture content. Test method: Sika®-Tramex meter, ≤ 4% pbw moisture content. Test method: CM - measurement or Oven-dry-method. No rising moisture according to ASTM (Polyethylene-sheet)</p>
Dew Point	<p>Beware of condensation!</p> <p>The substrate temperature must be at least 3°C above dew point to reduce the risk of de-lamination due to condensation.</p>
Application Instructions	
Mixing	<p>Part A : Part B = 50 : 50 (by volume)</p> <p>Dose and mix with suitable air driven or electrical two-part hot spray equipment. Both components must be heated up to +70°C.</p> <p>The accuracy of mixing and dosage must be controlled regularly with the equipment.</p> <p>Sikalastic®-841 ST might not be diluted under any circumstances. Thoroughly mix Sikalastic®-841 ST part B resin material using a drum mixer until a homogenous mixture and colour is obtained.</p>

Application Method / Tools

Prior to application, confirm substrate moisture content, r.h and dew point.

Primer:

Prime prepared concrete with Sikafloor®-156 or Sikafloor®-161 or Sika® Concrete Primer. Primer should not just be rolled or poured. In order to avoid the formation of pinholes, the primer must be brushed into the concrete surface, if necessary in two applications. Broadcasting with quartz sand 0.3 - 0.8 mm is optional, e.g. for flooring applications where high shear resistance is required. In order to avoid the formation of blisters do not broadcast to excess.

Waterproofing:

Apply using a plural component, heated, high pressure, proportioning spray equipment as those manufactured by Graco® GlasCraft® Gusmer, Wiwa®, Gama or any other equipment producer.

The proportioning equipment utilized must be capable of supplying correct pressure and heat for the appropriate hose length on a consistent basis.

Cleaning of Tools

Clean all tools and application equipment with Thinner C immediately after use. Hardened and/or cured material can only be removed mechanically

Waiting Time / Overcoating

Before applying Sikalastic®-841 ST on Sikafloor®-156ZA/ Sikafloor®-161 (with broadcasting) or SikaCor®EG 1 allow:

Substrate temperature	Minimum	Maximum
+10°C	24 hours	3 days ^{1,2)}
+20°C	20 hours	48 hours ^{1,2)}
+30°C	16 hours	24 hours ^{1,2)}
+40°C	14 hours	24 hours ^{1,2)}

Before applying Sikalastic®-841 ST on Sika® Concrete Primer allow:

Substrate temperature	Minimum	Maximum
+10°C	2 hours	24 hours ^{1,2)}
+20°C	1 hour	
+30°C	30 minutes	
+40°C	30 minutes	

Before applying Sikalastic®-841 ST on Sikalastic®-841 ST allow:

Substrate temperature	Minimum	Maximum
+10°C	10 sec.	6 hours ²⁾
+20°C		5 hours ²⁾
+30°C		4 hours ²⁾
+40°C		3 hours ²⁾

¹⁾ Assuming that any dirt has been carefully removed and contamination is avoided.

²⁾ If the max. waiting time is exceeded then hand abrade the entire surface using a moderate 200 to 300 grit sandpaper. Clean the grinded surface using Sika Colma®-Reiniger. For larger areas Sikalastic®-810 + 15% Thinner C must be applied as a bonding bridge.

Times are approximate and will be affected by changing ambient conditions particularly temperature and relative humidity.

Notes on Application / Limitations

This product may only be used by experienced professionals.

For spray application the use of protective health & safety equipment is mandatory!

Application by using plural component, heated, high pressure, proportioning spray equipment. Temperature of the substrate during application and curing: min. -15°C.

Lightly broadcasting provides higher adhesion values and extends the maximum waiting time of primer prior to the application of Sikalastic®-841 ST.

Under direct UV-exposure Sikalastic®-841 ST will discolour and may exhibit some chalking tendencies, but the mechanical properties are not affected. Where colour stability is required an appropriate top coat has to be applied.

Please note: Always apply a test area first.

Curing Details

Applied Product ready for use

Temperature	Rain resistant after	Ready for foot ¹⁾ traffic (carefully)	Ready for traffic ²⁾
+10°C	~ 2 minutes	~ 8 minutes	~ 90 minutes
+20°C		~ 5 minutes	~ 60 minutes
+30°C		~ 4 minutes	~ 45 minutes
+40°C		~ 3 minutes	~ 30 minutes

Note:

¹⁾ Only for inspection or for application of the next layer.

²⁾ Only for inspection, application of the next layer Not for permanent traffic.

Times are approximate and will be affected by changing ambient conditions.

Value Base

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

Local Restrictions

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

Health and Safety Information

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.

Legal Notes

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request or access on the Internet under www.sika.co.za.



Sika South Africa (Pty) Ltd
9 Hocking Place,
Westmead, 3608
South Africa

E-mail: headoffice@za.sika.com
Phone +27 31 792 6500
Telefax +27 31 700 1760
www.sika.co.za

