

PRODUCT DATA SHEET

Sikasil® C

Alcoxy silicone sealant for construction and sanitary applications

DESCRIPTION

Sikasil® C is a 1-component, non-corrosive multipurpose sealant for indoor and outdoor applications.

USES

Sikasil® C is designed for glazing and connection joints. Sikasil® C adheres well to metals, concrete, painted surfaces, wood, plastics, polycarbonates, ceramic tiles and is suitable for most sanitary applications.

CHARACTERISTICS / ADVANTAGES

- Faint odor
- Non-corrosive
- High elasticity and flexibility
- Long term fungus and mildew resistance
- Very good UV and weathering resistance
- Primer-less adhesion to a wide range of substrates

APPROVALS / STANDARDS

- ISO 11600 F 25 LM
- ISO 11600 G 25 LM
- EN 15651-1 F EXT-INT CC
- EN 15651-2 G CC
- EN 15651-3 S

PRODUCT INFORMATION

Chemical Base	Alcoxy silicone
Packaging	300 ml cartridges, 12 cartridges per box
Colour	Colour range to be defined by local sales organization.
Shelf Life	Sikasil® C has a shelf life of 15 months from the date of production, if it is stored properly in undamaged, original, sealed packaging, and if the storage conditions are met.
Storage Conditions	Sikasil® C shall be stored in dry conditions, protected from direct sunlight and at temperatures between +5 °C and +25 °C.
Density	1.00 kg/l approx. (ISO 1183-1)

TECHNICAL INFORMATION

Shore A Hardness	20 approx. (after 28 days)	(ISO 868)
Tensile Strength	1.6 N/mm ²	(ISO 8339)
Secant Tensile Modulus	0.35 N/mm ² at 100% elongation (23 °C)	(ISO 8339)

Elongation at Break	610% approx.	(ISO 37)
Elastic Recovery	> 70%	(ISO 7389)
Tear Propagation Resistance	3.1 N/mm approx.	(ISO 34)
Movement Capability	± 25%	(ISO 9047)
Service Temperature	-40 °C to +150 °C	
Joint Design	The joint width must be designed to suit the joint movement required and the movement capability of the sealant. For joints ≥ 10 mm and ≤ 20 mm wide, a joint depth of 10 mm is recommended. For larger joints please contact our Technical Service Department.	

APPLICATION INFORMATION

Consumption	Joint length [m] per 300 ml	Joint width [mm]	Joint depth [mm]
	3.0	10	10
2.0	15	10	
1.5	20	10	

Sag Flow	< 1 mm approx. (20 mm profile, 23 °C)	(ISO 7390)
Ambient Air Temperature	+5 °C to +40 °C, min. 3 °C above dew point temperature	
Substrate Temperature	+5 °C to +40 °C	
Curing Rate	3.5 mm/24 hours approx. (23 °C / 50% r.h.)	(CQP 049-2)
Skin Time	35 minutes approx. (23 °C / 50% r.h.)	(CQP 019-1)

APPLICATION INSTRUCTIONS

SUBSTRATE PREPARATION

The substrate must be clean, dry, sound and homogeneous, free from oils, grease, dust and loose or friable particles. Paint, cement laitance and other poorly adhering contaminants must be removed. Sikasil® C adheres without primers and/or activators. However, for optimum adhesion and critical, high performance applications, such as on multi-story buildings, highly stressed joints, extreme weather exposure or water immersion, the following priming and/or pre-treatment procedures shall be followed:

Aluminium, anodised aluminium, stainless steel, galvanised steel, powder coated metals or glazed tiles have to be cleaned and pre-treated using Sika® Aktivator-205, wiped on with a clean towel. Before sealing, allow a flash-off time of > 15 minutes (< 6 hours). Other metals, such as copper, brass and titanium-zinc, also have to be cleaned and pre-treated using Sika® Aktivator-205, wiped on with a clean towel. After the necessary flash-off time, use a brush to apply Sika® Primer-3 N and allow a further flash-off time of > 30 minutes (< 8 hours) before sealing the joints. PVC has to be cleaned and pre-treated using Sika® Primer-215 applied with a brush. Before sealing, allow a flash-off time of > 30 minutes (< 8 hours). Glass shall be cleaned with isopropyl alcohol before application.

Note: Primers are adhesion promoters. They are neither a substitute for the correct cleaning of a surface, nor do they improve the strength of the surface significantly.

For more detailed advice and instructions please contact our Technical Service Department.

APPLICATION METHOD / TOOLS

Sikasil® C is supplied ready to use.

After the necessary substrate preparation, insert a suitable backing rod to the required depth and apply any primer if necessary. Insert a cartridge into the sealant gun and extrude Sikasil® C into the joint making sure that it comes into full contact with the sides of the joint and avoids any air entrapment. Sikasil® C sealant must be firmly tooled against the joint sides to ensure adequate adhesion.

It is recommended to use masking tape where exact joint lines or neat lines are required. Remove the tape within the skin time. Do not use tooling products containing solvents.

CLEANING OF TOOLS

Clean all tools and application equipment immediately after use with Sika® Remover-208 and/or Sika® Top-Clean T. Once cured, residual material can only be removed mechanically.

FURTHER DOCUMENTS

- Safety Data Sheet
- Pre-treatment Chart Sealing and Bonding

LIMITATIONS

- Do not use Sikasil® C on bituminous substrates, natural rubber, EPDM rubber or on any building materials which might bleed oils, plasticizers or solvents that could attack the sealant.
- Do not use in totally confined spaces, Sikasil® C requires atmospheric moisture to cure.
- Sikasil® C is not recommended for porous substrates, such as concrete, stone, marble and granite. Bleeding can occur when Sikasil® C is used on these substrates.
- Sikasil® C is not recommended for use on submerged joints, joints where physical abuse or abrasion are likely to occur, structural glazing or insulated glazing, and food contact applications.
- Do not use Sikasil® C for medical or pharmaceutical uses.

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

ECOLOGY HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request. It may be necessary to adapt the above disclaimer to specific local laws and regulations. Any changes to this disclaimer may only be implemented with permission of Sika® Corporate Legal in Baar.

Sika South Africa (Pty) Ltd

9 Hocking Place,
Westmead, 3608
South Africa
Phone +27 31 792 6500
www.sika.co.za



Product Data Sheet

Sikasil® C
September 2020, Version 03.01
02051403000000020

SikasilC-en-ZA-(09-2020)-3-1.pdf