

## PRODUCT DATA SHEET

## SikaGrind®-116 RM ZA

## HIGH EFFICIENCY GRINDING AID FOR RAW MILL

## DESCRIPTION

SikaGrind®-116 RM ZA is a liquid aid for application in raw mill.  
SikaGrind®-116 RM ZA has been specifically designed to increase the output of raw materials grinding plant.

## USES

SikaGrind®-116 RM ZA is used in the grinding of raw materials to:

- Improve the product rate of raw materials comminution system

## CHARACTERISTICS / ADVANTAGES

SikaGrind®-116 RM ZA is a dispersant with the following characteristics:

- Neutralisation of electrical charges on the surface of raw material particles
- Separation of the raw material particles

SikaGrind®-116 RM ZA provides the following advantages in the raw material comminution process:

- Enhanced grinding properties of raw material mill due to less accumulation of material on grinding media
- Higher separator efficiency due to improved raw material particles dispersion
- Reduced relative power consumption due to increased output of the grinding system (tons per hour)
- Easier achievement of the desired fineness of ground raw material due to reduced re-agglomeration of the sufficiently ground raw material particles
- Minimized problems with “plugging” due to improved powder flow characteristics

SikaGrind®-116 RM ZA gives the following advantages to the finished raw material:

- Reduced quantity of “over-milled” particles in raw material granulometry
- Easier discharge of ground raw material particles

## PRODUCT INFORMATION

Chemical Base	Organic & inorganic solutions
Packaging	1000 L IBC (Bulk upon request)
Appearance / Colour	Brown liquid
Shelf Life	At least 12 months
Storage Conditions	Store in undamaged, unopened and sealed original containers when Shelf-Life stored at temperatures between +5°C and +35°C. Protect from direct sunlight and contamination.
Density	1.116 ± 0.03 kg/L

# APPLICATION INFORMATION

Recommended Dosage	Typical dosage rates of SikaGrind®-116 RM ZA are between 400 – 800 ppm of raw material .The optimum dosage to achieve the desired characteristics shall be determined in plant trials. For consistent results, SikaGrind®-116 RM ZA must be accurately dispensed.
Dispensing	SikaGrind®-116 RM ZA is added onto the raw material mill feed shortly before the mill entrance or directly into the grinding mill (first or second compartment). Suitable dosage pumps with adjustable flow rates shall be used for accurate dosing. Note: Periodically, the end of the additive tube/hose shall be checked to ensure, that it is not blocked!

## BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## ECOLOGY HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

## LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika’s current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika’s recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product’s suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika South Africa (Pty) Ltd  
9 Hocking Place,  
Westmead, 3608  
South Africa  
Phone +27 31 792 6500  
www.sika.co.za



Product Data Sheet  
SikaGrind®-116 RM ZA  
July 2025, Version 01.01  
021407011000245203

SikaGrind-116RMZA-en-ZA-(07-2025)-1-1.pdf