

PRODUCT DATA SHEET

Sikalastic®-702

Elastic polyurea hybrid liquid applied membrane for roof waterproofing

DESCRIPTION

Sikalastic®-702 is a 2-part, elastic, hybrid polyurea based liquid applied roof waterproofing membrane. It is part of the SikaRoof® PUR liquid applied roofing solutions range of products.

USES

Sikalastic®-702 may only be used by experienced professionals.

Sikalastic®-702 may only be used by experienced professionals.

Designed for the following roof waterproofing applications:

- Flat fully exposed roof structures
- New construction and refurbishment projects
- Roofs with numerous details such as penetrations, drains, roof lights and complex geometry
- Balcony and terrace decks underneath a protective layer (i.e. ballast, paving slabs, tiles)
- Alternative option for small projects where application machinery is not practical

CHARACTERISTICS / ADVANTAGES

- Cold applied - requires no heat or flame
- One layer application
- High elasticity and elongation at break
- No reinforcement required
- Self-smoothing
- Applied by notched rubber or metal squeegees
- Good adhesion to many substrates with the appropriate primers
- Can be covered with an aliphatic top coat
- Resistant to ponding water

APPROVALS / STANDARDS

- Root resistance DIN CEN/TS 14416, Sikalastic®-702, kiwa, Test report No. 0078.0.1-2019e
- CE Marking and Declaration of Performance to ETAG 005-1-6:2004, Liquid-applied roof waterproofing using kits based on polyurethane
- Fire Testing EN 13501-5, Sikalastic®-701, warrington-fire, Report No. 19895B, 19895C
- Fire Testing EN 13501-1, Sikalastic®-701 warrington-fire, Report No.19896B

PRODUCT INFORMATION

Chemical Base	Elastomeric PU/PUA hybrid	
Packaging	Parts A+B: 20.1 L (25 kg) Part A Part B	
	4.7 L (9.2 kg)	15.5 L (15.8 kg)
	Refer to current price list for packaging variations	
Colour	Dark grey When product is exposed to direct sunlight (UV), there may be some discolouration. Additional UV protection can be achieved by application of a topcoat: Sikalastic®-701 / 701 SF. This must be applied within 7 days over Sikalastic®-702 otherwise the performance may be affected.	
Shelf Life	12 months from date of production	

Storage Conditions	Product must be stored in original, unopened and undamaged packaging in dry conditions at temperatures between +5 °C and +30 °C. Always refer to packaging.
Density	~1.24 kg/L (Mixed A+B)
Volatile organic compound (VOC) content	~0.07 g/L
Solid content by weight	~100 % (Part A & B)
Solid content by volume	~100 % (Part A & B)

TECHNICAL INFORMATION

Shore A Hardness	~75
Resistance to Root Penetration	Root resistant
Tensile Strength	~10.0 N/mm ²
Elongation at Break	~900 %
Tensile Adhesion Strength	~2.5 N/mm ² Value measured using Sika® Concrete Primer LO
Tear Strength	~13.8 N/mm ²
External Fire Performance	B _{roof} T1 / B _{roof} T4 (ENV 1187)
Reaction to Fire	Euroclass E (EN 13501-1)
Chemical Resistance	Resistant to many chemical based cleaners. Contact Sika Technical Services for additional information.

APPLICATION INFORMATION

Mixing Ratio	Part A : Part B = 1 : 1.72 (by weight)																				
Product Temperature	+10 °C min. / +25 °C max.																				
Ambient Air Temperature	+2 °C min. / +40 °C max.																				
Relative Air Humidity	35 % r.h. min / 80 % r.h. max.																				
Dew Point	Beware of condensation. The substrate and uncured applied membrane must be at least +3 °C above dew point to reduce the risk of condensation or blooming on the membrane finish.																				
Substrate Temperature	+2 °C min. / +40 °C max.																				
Substrate Moisture Content	The product can be applied on substrates with a moisture content of ≤ 4 % part by weight. The substrate must be visibly dry with no standing water. The following test methods can be used to determine the substrate moisture content: <ul style="list-style-type: none"> ▪ Sika®-Tramex meter ▪ CM-measurement ▪ Oven-dry-method No rising moisture according to ASTM (Polyethylene-sheet).																				
Pot Life	~25 minutes at +20 °C Pot life will decrease at higher temperatures and increase at lower temperatures.																				
Applied Product Ready for Use	<table border="1"> <thead> <tr> <th>Temperat- ure</th> <th>Relative Hu- midity</th> <th>Rain Resist- ant</th> <th>Foot Traffic/Over- coating</th> <th>Full Cure</th> </tr> </thead> <tbody> <tr> <td>+10 °C</td> <td>~50 %</td> <td>~3 hours</td> <td>~10 hours</td> <td>~28 hours</td> </tr> <tr> <td>+20 °C</td> <td>~50 %</td> <td>~2 hours</td> <td>~6 hours</td> <td>~24 hours</td> </tr> <tr> <td>+30 °C</td> <td>~50 %</td> <td>~1 hour</td> <td>~4 hours</td> <td>~20 hours</td> </tr> </tbody> </table>	Temperat- ure	Relative Hu- midity	Rain Resist- ant	Foot Traffic/Over- coating	Full Cure	+10 °C	~50 %	~3 hours	~10 hours	~28 hours	+20 °C	~50 %	~2 hours	~6 hours	~24 hours	+30 °C	~50 %	~1 hour	~4 hours	~20 hours
Temperat- ure	Relative Hu- midity	Rain Resist- ant	Foot Traffic/Over- coating	Full Cure																	
+10 °C	~50 %	~3 hours	~10 hours	~28 hours																	
+20 °C	~50 %	~2 hours	~6 hours	~24 hours																	
+30 °C	~50 %	~1 hour	~4 hours	~20 hours																	

SYSTEM INFORMATION

System Structure	System <ul style="list-style-type: none">▪ Sikalastic®-702▪ Refer to the System Data Sheet: SikaRoof® PUR Systems▪ Primers Substrate <table><tr><td>Cementitious substrates</td><td>Primer Sika® Concrete Primer LO or Sika-floor®-161 lightly broadcast with quartz sand, 0.3–0.8 mm</td></tr><tr><td>Ceramic tiles (unglazed), and concrete slabs</td><td>Sika® Concrete Primer LO</td></tr><tr><td>Bituminous felt</td><td>Sikalastic® Metal Primer N</td></tr><tr><td>Bituminous coatings</td><td>Sikalastic® Metal Primer N</td></tr><tr><td>Metals & Ferrous or galvanised metals, lead, copper, aluminium, brass or stainless steel</td><td>Sikalastic® Metal Primer N</td></tr></table>	Cementitious substrates	Primer Sika® Concrete Primer LO or Sika-floor®-161 lightly broadcast with quartz sand, 0.3–0.8 mm	Ceramic tiles (unglazed), and concrete slabs	Sika® Concrete Primer LO	Bituminous felt	Sikalastic® Metal Primer N	Bituminous coatings	Sikalastic® Metal Primer N	Metals & Ferrous or galvanised metals, lead, copper, aluminium, brass or stainless steel	Sikalastic® Metal Primer N
Cementitious substrates	Primer Sika® Concrete Primer LO or Sika-floor®-161 lightly broadcast with quartz sand, 0.3–0.8 mm										
Ceramic tiles (unglazed), and concrete slabs	Sika® Concrete Primer LO										
Bituminous felt	Sikalastic® Metal Primer N										
Bituminous coatings	Sikalastic® Metal Primer N										
Metals & Ferrous or galvanised metals, lead, copper, aluminium, brass or stainless steel	Sikalastic® Metal Primer N										
	For the primer consumption rates and waiting time / overcoating, refer to the appropriate Product Data Sheet. Other substrates must be tested for their compatibility. If in doubt, apply a test area first.										
Dry film thickness	Refer to the System Data Sheet: SikaRoof® PUR Systems										
System Performance	Refer to the System Data Sheet: SikaRoof® PUR Systems										

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

FURTHER DOCUMENTS

- Sika Method Statement: SikaRoof® PUR roof waterproofing systems

LIMITATIONS

Installation work must only be carried out by Sika trained and approved contractors, experienced in this type of application.

- Products must only be applied in accordance with their intended use.
- Do not apply on substrates with rising moisture.

ECOLOGY HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

SUBSTRATE PREPARATION

- The supporting structure must be of sufficient structural strength to apply all new and existing layers of the roof build-up. Complete roof system must be designed and secured against wind uplift loadings.
- Refer to the Sika Method Statement: SikaRoof® PUR roof waterproofing systems
- Suitable substrates: Concrete, bituminous felts and coatings, metal, brickwork, asbestos cement, ceramic tiles.

MIXING

Refer to the Sika Method Statement: SikaRoof® PUR roof waterproofing systems

APPLICATION

Strictly follow installation procedures as defined in method statements, application manuals and working instructions which must always be adjusted to the actual site conditions.

Refer to the Sika Method Statement: SikaRoof® PUR roof waterproofing systems

CLEANING OF TOOLS

Clean all tools and application equipment with Thinner C or similar, immediately after use. Hardened material can only be removed mechanically.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika South Africa (Pty) Ltd
9 Hocking Place,
Westmead, 3608
South Africa
Phone +27 31 792 6500
www.sika.co.za



Product Data Sheet
Sikalastic®-702
February 2026, Version 05.01
020915505000000014

Sikalastic-702-en-ZA-(02-2026)-5-1.pdf

BUILDING TRUST

