

product data sheet Sikasil[®] WS-605 S

HIGH-PERFORMANCE, NON-STREAKING SILICONE WEATHERPROOFING SEALANT, CE-MARKED

TYPICAL PRODUCT DATA (FURTHER VALUES SEE SAFETY DATA SHEET)

Chemical base		1-component silicone	
Color (CQP001-1)		Various colors available ^A	
Cure mechanism		Moisture-curing	
Cure type		Neutral	
Density (uncured)		1.5 kg/l	
Non-sag properties (CQP061-4 / ISO 7390)		good	
Application temperature	ambient	5 – 40 °C	
Skin time (CQP019-1)		25 minutes ^B	
Tack free time (CQP019-3)		120 minutes ^B	
Curing speed (CQP049-1)		(see diagram)	
Shore A hardness (CQP023-1 / ISO 7619-1)		30 ^c	
Tensile strength (CQP036-1 / ISO 527)		1.0 MPa	
100 % modulus (CQP036-1 / ISO 527)		0.3 MPa	
Elongation at break (CQP036-1 / ISO 527)		800 %	
Tear propagation resistance (CQP045-1 / ISO 34)		4.0 N/mm	
Service temperature		-40 – 150 °C	
Shelf life (CQP016-1)	cartridge / unipack	12 months ^D	
	pail / drum	6 months ^D	

CQP = Corporate Quality Procedure ^{C)} after 28 days

DESCRIPTION

Sikasil[®] WS-605 S is a durable, neutral-curing silicone sealant with a high movement capability and excellent adhesion to a wide range of substrates. Non-streaking properties on non-porous substrates. It is particularly suited as a weather seal for structural glazing, curtain walling and windows.

 $^{\rm A)}$ color defined by local sales organization $^{\rm D)}$ storage below 25 °C

^{B)} 23 °C / 50 % r. h.

PRODUCT BENEFITS

- Meets requirements of ISO 11600 F 25 LM & G 25 LM, EN 15651-1 F EXT-INT CC 25LM, EN 15651-2 G CC 25LM, ASTM C 920 for Type S, Grade NS, Class 50 (movement capability ± 50 %), ASTM C 1248, AENOR Marca N F+G 25 LM
- Provided with CE-mark according to EN 15651-1:2012, F EXT-INT CC 25LM, EN 15651-2:2012, G CC 25LM, certified by Control Body 1119
- SNJF F&V 25 E (product code: 2885, 2891)
- Non-streaking on non-porous substrates
- Outstanding UV and weathering resistance
- Adheres well to glass, metals, coated / painted metals, plastics and wood

AREAS OF APPLICATION

Sikasil[®] WS-605 S can be used for weatherproofing and sealing applications where durability under severe conditions is required. It is particularly suited as a weather seal for structural glazing, curtain walling and windows.

This product is suitable for experienced professional users only. Tests with actual substrates and conditions have to be performed to ensure adhesion and material compatibility.



PRODUCT DATA SHEET Sikasil® WS-605 S Version 03.01 (04 - 2020), en_ITSES 012603206059001000

CURE MECHANISM

Sikasil[®] WS-605 S cures by reaction with atmospheric moisture. At low temperatures the water content of the air is generally lower and the curing reaction proceeds some-what slower (see diagram 1).

The curing speed of the reaction depends mainly on the relative humidity and temperature. Material temperature above 50 °C could lead to bubble formation and has to be avoided.



Diagram 1: Curing speed Sikasil® WS-605 S

METHOD OF APPLICATION

Surface preparation

Surfaces must be clean, dry and free from grease, oil and dust. Surface treatment depends on the specific nature of the substrates and is crucial for a long lasting bond.

Application

The optimum temperature for substrate and sealant is between 15 °C and 25 °C.

Sikasil[®] WS-605 S can be processed with hand, pneumatic or electric driven piston guns as well as pump equipment. For advice on selecting and setting up a suitable pump system, contact the System Engineering Department of Sika Industry.

Joints must be properly dimensioned.

For optimum performance the joint width needs to be designed according to the movement capability of the sealant based on the actual expected movement. The minimum joint depth is 6 mm and a width / depth ratio of minimum 2 : 1 and maximum 4 : 1 must be respected. Joints deeper than 15 mm must be avoided.

For backfilling it is recommended to use closed cell, sealant compatible foam backer rods e.g. high resilience polyethylene foam rod. If joints are too shallow for backing material to be employed, we recommend using a polyethylene tape. This acts as a release film (bond breaker), allowing the joint to move and the silicone to stretch freely.

Tooling and finishing

Tooling and finishing must be carried out within the skin time of the sealant or adhesive.

When tooling freshly applied Sikasil[®] WS-605 S, press the adhesive to the joint flanks to get a good wetting of the bonding surface. No tooling agents must be used.

Removal

Uncured Sikasil® WS-605 S can be removed from tools and equipment with Sika® Remover-208 or another suitable solvent. Once cured, the material can only be removed mechanically.

Hands and exposed skin have to be washed immediately using hand wipes such as Sika[®] Cleaner-350H cleaning towels or a suitable industrial hand cleaner and water. Do not use solvents on skin.

Overpainting

Sikasil® WS-605 S cannot be overpainted.

Application limits

Most Sikasil[®] WS, SG, IG and WT, silicones manufactured by Sika are compatible with each other. For specific information regarding compatibility between various Sikasil[®] products contact the Technical Department of Sika Industry.

To exclude materials influencing Sikasil[®] WS-605 S, all materials such as gaskets, tapes, setting blocks, sealants, etc., in direct and indirect contact have to be approved by Sika in advance.

Where two or more different reactive sealants are used, allow the first to cure completely before applying the next. Sikasil® WS-605 S may only be used in combination with structural glazing applications after a detailed examination of the corresponding project details.

Do not use Sikasil[®] WS-605 S on PMMA and PC elements as it may cause environmental stress cracking (crazing).

FURTHER INFORMATION

The information herein is offered for general guidance only. Advice on specific applications is available on request from the Technical Department of Sika Industry.

Copies of the following publications are avail-

able on request:

 Safety Data Sheets
General Guideline Sikasil[®] Weather Sealants

PACKAGING INFORMATION

Cartridge	300 ml
Unipack	400 ml
Unipack	600 ml
Pail	26 kg
Drum	280 kg

BASIS OF PRODUCT DATA

All technical data stated in this document are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

HEALTH AND SAFETY INFORMATION

For information and advice regarding transportation, handling, storage and disposal of chemical products, users shall refer to the actual Safety Data Sheets containing physical, ecological, toxicological and other safety-related data.

DISCLAIMER

The information, and, in particular, the recommendations relating to the application and enduse of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

PRODUCT DATA SHEET Sikasil® WS-605 S Version 03.01 (04 - 2020), en_ITSES 012603206059001000 Sika Engineering Silicones Srl Via L. Einaudi 6 20068 Peschiera Borromeo (MI) - Italia Tel.: +39 02 516591 205 it-ses-admin@it.sika.com www.sika.com/ses





