

PRODUCT DATA SHEET

SikaGrind®-160 MY

STRENGTH ENHANCING GRINDING AID FOR THE PRODUCTION OF CEMENT

DESCRIPTION

SikaGrind®-160 MY is a liquid cement grinding aid with performance enhancing properties.

SikaGrind®-160 MY has been specifically designed to increase the output of cement grinding plants and obtain improved strength development for cements

USES

- Improve the production rate of the cement grinding system
- Increase the **early and final strength** of the cement

CHARACTERISTICS / ADVANTAGES

SikaGrind®-160 MY is a dispersant with the following characteristics:

- Neutralisation of electrical charges on the surface of the cement particles

- Separation of the cement particles

SikaGrind®-160 MY provides the following advantages in the cement production:

- Enhanced grinding properties of the cement mill due to less accumulation of material on grinding balls and mill-liners
- Higher separator efficiency due to improved cement particle dispersion
- Reduced relative power consumption per ton of cement due to increased output of the grinding system (tons per hour)
- Easier achievement of the desired cement
- Improved powder flow characteristics

SikaGrind®-160 MY gives the following advantages to the finished cement:

- Reduced quantity of “over-milled” particles in the cement granulometry
- Easier discharge of the silos
- Increased **early and final strengths**
- Economic cement design with clinker replacements

PRODUCT INFORMATION

Chemical Base	Aqueous blend of minerals and polymers
Packaging	1 000 kg IBC Bulk deliveries
Appearance / Colour	Brown liquid
Shelf Life	12 months from date of production
Storage Conditions	Store in undamaged, unopened and sealed original containers at temperatures between +5 °C and +35 °C. Protect from frost, direct sunlight and contamination. Note: When delivered in bulk, the tanks and equipment used must be free from contaminants.
Density	1.17 ± 0.02 kg/l (at +20°C)

APPLICATION INFORMATION

Recommended Dosage

Typical dosage rates of SikaGrind®-160 MY is between 0.2–1.0 kg per tonne of cement (0.02–0.10 % of total weight = cement clinker + additions). The optimum dosage to achieve the desired characteristics shall be determined in Plant trials. Influencing factors are e.g. the properties of clinker source, type of cement and other plant variables.

For consistent results, SikaGrind®-160 MY must be accurately dispensed.

Compatibility

Cements treated with SikaGrind®-160 MY are compatible in concretes produced with all commercial admixtures including air entrainers, water reducers, retarders and superplasticizers. The performance of concrete admixtures is not adversely affected by the use of SikaGrind®-160 MY.

APPLICATION INSTRUCTIONS

DISPENSING

SikaGrind®-160 MY is added onto the clinker feed shortly before the mill entrance or directly into the grinding mill (first or second compartment). Suitable dosage pumps with adjustable flow rates shall be used for accurate dosing.

Note: Periodically, the end of the additive tube/hose shall be checked to ensure that it is not blocked!

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

ECOLOGY HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer

to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request. It may be necessary to adapt the above disclaimer to specific local laws and regulations. Any changes to this disclaimer may only be implemented with permission of Sika® Corporate Legal in Baar.

Sika South Africa (Pty) Ltd

9 Hocking Place,
Westmead, 3608
South Africa
Phone +27 31 792 6500
www.sika.co.za



Product Data Sheet

SikaGrind®-160 MY
August 2020, Version 01.02
021407021000000462

SikaGrind-160MY-en-ZA-(08-2020)-1-2.pdf