

PRODUCT DATA SHEET

Sikaflex® Construction Purform®

Low-modulus sealant for concrete and masonry facades

DESCRIPTION

Sikaflex® Construction Purform® is a 1-part, non-sag, elastic polyurethane joint sealant. Due to its good application properties and high movement capability it durably seals movement and connection joints in concrete and masonry facades.

USES

The Product is used for elastic joint sealing and weatherproofing of movement and connection joints in building envelopes.

Sikaflex® Construction Purform® is used for the following application areas:

- Around window and door frames
- Around facade elements
- Around precast elements
- EIFS facades

Sikaflex® Construction Purform® is used for interior and exterior applications.

CHARACTERISTICS / ADVANTAGES

- Easy to extrude and tool
- High movement capability: $\pm 25\%$ (ISO 9047), $\pm 50\%$ (ASTM C719)
- Low stress on substrate due to the low modulus of the sealant
- Good resistance to weathering
- Good mechanical resistance
- Good adhesion to many construction materials
- Monomeric diisocyanate content $< 0.1\%$: no user safety training needed (REACH restriction 2023, Annex XVII entry 74)

ENVIRONMENTAL INFORMATION

- Contributes towards satisfying Indoor Environmental Quality (EQ) Credit: Low-Emitting Materials under LEED® v4
- VOC emission classification GEV Emission EC1^{plus}

APPROVALS / STANDARDS

- VOC Content SCAQMD Rule 1168, Sikaflex® - , eurofins, Test Report No. 392-2023-00524602_XG_EN
- VOC EMISSION M1, Sikaflex® xx, eurofins, Test Report No. 392-2022-00437201_I_EN
- Classification for sealants DIN EN ISO 11600, Sikaflex®-708 Construction, SKZ, Test Report No. 225964/22-III

PRODUCT INFORMATION

Product Declaration	EN 15651-1:2012	F EXT-INT CC 25 LM
	ISO 11600:2002	Class F 25 LM
	ASTM C 920-18	Movement Class 50
Chemical Base	Sika® Purform® polyurethane	
Packaging	300 ml cartridge	12 cartridges per box
	600 ml foil pack	20 foil packs per box
Refer to the current price list for available packaging variations.		
Shelf Life	15 months from date of production	
Storage Conditions	The Product must be stored in original, unopened and undamaged sealed packaging in dry conditions at temperatures between +5 °C and +30 °C. Always refer to the packaging. Refer to the current Safety Data Sheet for information on safe handling and storage.	
Colour	Available in a range of colours, refer to the price list for further information.	
Density	(1.45 ± 0.1) kg/l	(ISO 1183-1)

TECHNICAL INFORMATION

Shore A Hardness	Cured 28 days at +23 °C and 50 % R.H.	> 20	(EN ISO 868)
Tensile Strength	Cured 28 days at +23 °C and 50 % R.H.	0.96 MPa	(ISO 37)
Secant Tensile Modulus	Cured 28 days at +23 °C and 50% R.H. Measured at 100% elongation at +23 °C	0.30 N/mm ²	(ISO 8339)
	Cured 28 days at +23 °C and 50% R.H. Measured at 100% elongation at -20 °C	0.60 N/mm ²	
Elongation at Break	Cured 7 days at +23 °C and 50 % R.H. Measured at 100 % elongation at -20 °C	1000 %	(ISO 37)
Movement Capability	± 25 %		(EN ISO 9047)
	± 50 %		(ASTM C719)
Elastic Recovery	Cured 28 days at +23 °C and 50 % R.H.	90 %	(EN ISO 7389)
Tear Propagation Resistance	Cured 28 days at +23 °C and 50 % R.H.	6.0 N/mm	(ISO 34-2)
Service Temperature	Maximum	+70 °C	
	Minimum	-40 °C	
Resistance to Weathering	10		(ISO 19862)

Joint Design

For movement joints, the width must be at least 8 mm and should not exceed 40 mm. For non-movement joints such as connection joints in interior areas, the joint width can be less than 8 mm.

The joint dimensions must be designed to suit the movement capability of the sealant. In all cases joints must be at least 8 mm deep or have a width to depth ratio of 2 : 1 whichever is greater.

For more information about joint design and calculations refer to the Sika document Design guideline: Dimensioning of construction joints or contact Sika Technical Services.

APPLICATION INFORMATION

Sag Flow	20 mm profile tested at +50 °C	0 mm	(EN ISO 7390)
Product Temperature	Maximum	+40 °C	
	Minimum	+5 °C	
Ambient Air Temperature	Maximum	+30 °C	
	Minimum	+5 °C	
Substrate Temperature	Maximum	+40 °C	
	Minimum	+5 °C	
Beware of condensation. Substrate temperature during application must be at least +3 °C above dew point.			
Backing Material	Use closed cell, polyethylene foam backing rod.		
Curing Rate	At +23 °C and 50 % R.H.	3 mm / 24 h	(CQP049-2)
Skin Time	At +23 °C and 50 % R.H.	60 minutes	(CQP019-1)
Tooling Time	At +23 °C and 50 % R.H.	40 minutes	(CQP019-2)

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

ECOLOGY HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

SUBSTRATE PREPARATION

IMPORTANT

Poor adhesion due to inadequate surface preparation

Primers are adhesion promoters.

1. Do not use primers for improving poorly prepared or poorly cleaned joint surfaces.

IMPORTANT

Poor adhesion due to incorrect priming procedure

Incorrectly defined or uncontrolled priming procedures may lead to a variation in Product performance.

1. Test adhesion on project-specific substrates and agree on procedures with all parties before full project application. For more information contact Sika Technical Services.

The substrate must be sound, clean, dry and free of contaminants such as dirt, oil, grease, cement laitance, sealant residues and poorly bonded coatings which could affect adhesion of the primer and sealant.

The substrate must be of sufficient strength to cope with the stresses induced by the sealant during movement.

1. Use techniques such as wire brushing, grinding, grit blasting or other suitable mechanical methods to remove all weak substrate material.
2. Repair all damaged joint edges with suitable Sika repair products.
3. Remove dust, loose and friable material from all surfaces before applying the sealant.

If tested or supported by experience, the Product can be used without primers or activators on many substrates.

Use the following priming or pre-treatment procedures to ensure optimum adhesion and joint durability, or if the Product is used for high-performance applications such as joints on multi-storey buildings, highly stressed joints, or joints exposed to extreme weather.

NON-POROUS SUBSTRATES

Aluminium, anodised aluminium, stainless steel, galvanised steel or glazed tiles

1. Lightly roughen the surface with a fine abrasive pad.
2. Clean the surface.
3. Pretreat the surface with Sika® Aktivator-205 applied with a clean cloth.

Other metals, such as copper, brass and titanium-zinc

1. Lightly roughen the surface with a fine abrasive pad.
2. Clean the surface.
3. Pretreat the surface with Sika® Aktivator-205 applied with a clean cloth.
4. Wait until the flash-off time is over.
5. Prime the surface with Sika® Primer-3 N applied with a brush.

Powder-coated metals

1. Carry out preliminary trials to verify adhesion. For more information contact Sika Technical Services.

PVC substrates

1. Prime the surface with Sika® Primer-215 applied with a brush.

POROUS SUBSTRATES

Concrete, aerated concrete and cement based renders, mortars and bricks

1. Prime the surface with Sika® Primer-3 N or Sika® Primer-115 applied with a brush.

Concrete that is 2–3 days old, or matt wet (surface dry)

1. Prime the surface with Sika® Primer-115 applied with a brush.

APPLICATION

IMPORTANT

Strictly follow installation procedures

Strictly follow installation procedures as defined in Method Statements, application manuals and working instructions which must always be adjusted to the actual site conditions.

IMPORTANT

Staining on natural stone substrates due to plasticiser migration

Staining from plasticiser migration may occur when used on cast, reconstituted or natural stone such as granite, marble or limestone substrates.

1. Do not use on natural stone substrates

IMPORTANT

Degradation of sealant due to substrates leaching oil, plasticisers, or solvents

Bitumen, natural rubber or EPDM rubber can leach oils, plasticisers, or solvents that can degrade the sealant and cause the Product to become tacky.

1. Do not use the Product on building materials which leach oils, plasticisers, or solvents.

IMPORTANT

Degradation of sealant due to chemical attack

1. Do not use the Product to seal joints in and around swimming pools containing water treatment agents such as chlorine.

IMPORTANT

Insufficient curing due to exposure to alcohol

Exposure to alcohol during curing may interfere with the curing reaction and cause the Product to remain soft or become tacky.

1. Do not expose the Product to alcohol-containing products during the curing period.

IMPORTANT

Material malfunction caused by lack of air humidity

Air humidity is required for the Product to cure.

1. Make sure air humidity is sufficient so the material can cure and function properly.

Delayed skin formation and curing time due to changing ambient conditions

Note: Changing ambient conditions can affect product performance. Skin formation and curing time can be significantly delayed by low humidity, low temperature and large joint dimensions.

1. Apply masking tape where neat or exact joint lines are required.
2. After the required substrate preparation, insert a backing rod to the required depth.
3. Prime the joint surfaces as recommended in substrate preparation. Note Avoid excessive application of the primer.
4. Open the seal on the top of the cartridge or open the end of the foil pack.
5. Fit the nozzle and cut it to the desired bead size.
6. Insert the Product into the application gun.
7. Apply the Product into the joint. Note Avoid air entrapment. Make sure that the Product comes into full contact with the adhesion area of the joint.
8. **IMPORTANT** Do not use tooling products containing solvents. As soon as possible after application, tool the Product firmly against the joint sides to ensure adequate adhesion and a smooth finish. Use a compatible tooling agent such as Sika® Tooling Agent N to smooth the joint surface.
9. Remove the masking tape within the skin formation time of the Product.

OVERPAINTING THE SEALANT IMPORTANT

Tacky paint due to plasticiser migration

Paints and sealants or adhesives may contain plasticizers and other substances that migrate and can cause the painted surface to become tacky.

IMPORTANT

Cracking paint due to joint movement

Rigid paint applied on top of a sealant or flexible adhesive may crack when used on joints subject to movement.

The Product can be overpainted with most conventional paint coating systems.

1. Allow the Product to fully cure before overpainting.
2. Before overpainting, carry out preliminary trials to test compatibility of the paint or coating system with the Product in accordance with ISO/TR 20436:2017 – Buildings and civil engineering works — Sealants — Paintability and paint compatibility of sealants.

Colour variation

Note: Colour variation may occur especially with white or other light colour shades. This effect is purely aesthetic and does not adversely influence the technical performance or durability of the Product.

CLEANING OF TOOLS

Clean all tools and application equipment immediately after use with Sika® Remover-208 or Sika® Cleaning Wipes-100. Once cured, hardened material can only be removed mechanically.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika South Africa (Pty) Ltd

9 Hocking Place,
Westmead, 3608
South Africa
Phone +27 31 792 6500
www.sika.co.za



Product Data Sheet
Sikaflex® Construction Purform®
July 2024, Version 03.01
02051101000000123

SikaflexConstructionPurform-en-ZA-(07-2024)-3-1.pdf