

Sikafloor®-82 EpoCem®

3-part cement and epoxy combination mortar
for self-smoothing floor screeds of 3 to 7 mm

Construction

Product Description Sikafloor®-82 EpoCem® is a three part, epoxy modified cementitious, fine textured mortar for self smoothing floor screeds in layers of 3 to 7 mm.

Uses As a Temporary Moisture Barrier (TMB) (3 - 7 mm thick) allowing the application of Epoxy, Polyurethane and PMMA* resin floors requiring dry substrates, over high moisture content substrates, even green concrete, for a lasting solution.

As a self-smoothing screed for:

- Levelling or patching horizontal concrete surfaces, in new work or repairs, in aggressive chemical environments
- Floor topping on non ventilated damp substrates without particular aesthetic requirements
- Levelling layer under Epoxy, Polyurethane and PMMA* floor coatings / screeds, tiles, sheet floors, carpets or wooden floors
- Repair and maintenance of monolithic and vacuum concrete floors

Extended with quartz sand, as a patching and repair mortar:

- Under Epoxy, Polyurethane and PMMA floor coatings / screeds

Designed for use on cementitious substrates.

- Suitable for restoration work (Principle 3, method 3.1 of EN 1504-9).
- Suitable for structural strengthening (principle 4, method 4.4 of EN 1504-9).
- Suitable for preserving or restoring passivity (principle 7, method 7.1 and 7.2 of EN 1504-9).
- Suitable for increasing resistivity (Principle 8, method 8.3 of EN 1504-9)

* See Notes on Application / Limitations

Characteristics / Advantages

- Can be over coated with resin based floors after 24 hours (+20°C, 75% r.h.)
- Prevents osmotic blistering of resin based coatings over damp substrates
- Economical and fast, easy application
- Class R4 of EN 1504-3
- Good levelling properties
- Impervious to liquids but permeable to water vapour
- Compatible with bituminous overlays
- Frost and de-icing salt resistant



- Good chemical resistance
- Thermal expansion properties similar to concrete
- Excellent bond to green or hardened concrete whether damp or dry
- Excellent early and final mechanical strengths
- Excellent resistance to water and oils
- It is the ideal preparation for smooth surface finishes
- For internal or external use
- Contains no solvents
- Will not corrode reinforcement steel

Tests

Approval / Standards	ITT reports (*) for EN 1504-3 Ref. 09/352-966 dated May 4 th , 2009 by Applus Laboratory, Barcelona, Spain. * confirm with producing company
	Epoxy modified cementitious mortar for self smoothing floor screeds according to EN 1504-2: 2004 , EN 1504-3: 2005 and EN 13813:2002, DoP 02 08 02 01 002 0 000001 1001 , certified by Factory Production Control Body No. 0921, certificate 2017, and provided with the CE-mark

Product Data

Form

Appearance / Colours	Part A - resin: white liquid
	Part B - hardener: transparent yellowish liquid
	Part C - filler: natural grey aggregate
	Colour: light grey
	Finish: matt

Packaging	Pre-batched 27.5 kg units (13ltr)
	Part A: 1.00 kg plastic container
	Part B: 2.50 kg plastic container
	Part C: 24.00 kg aluminium lined double paper bags

Storage

Storage Conditions/ Shelf-Life	Part A, part B: 12 months
	Part C: 12 months
	From date of production if stored in original, unopened and undamaged sealed packaging, in dry conditions at temperatures between +5°C and +30°C.
	Part A, part B: Protect from frost
	Part C: Protect from humidity

Technical Data

Chemical Base	Epoxy modified cementitious mortar.
Density	Part A: ~ 1.05 kg/l (at +20°C)
	Part B: ~ 1.03 kg/l (at +20°C)
	Part C: ~ 1.97 kg/l (at +20°C)
	Parts A+B+C mixed: ~ 2.10 kg/l (at +20°C). (EN 1015-6)

Layer Thickness	3.0 mm minimum / 7.0 mm maximum
	If Sikafloor®-82 EpoCem® is used as a Temporary Moisture Barrier (TMB), a minimum of 3 mm must be applied.

Carbon Dioxide Diffusion Coefficient (μCO₂)	μCO ₂ ≈ 1782.- (SN EN 1062-6)
	Carbonation resistance for 8 mm thickness: R ≈ 24.2 m

Fire Rating	Class A2 _(fl) S1 (EN 13501-1)
--------------------	--

Service Temperature	-30°C to +80°C for continuous exposure
----------------------------	--

Mechanical / Physical Properties

Compressive Strength

(EN 13892-2)

	+23°C / 50% r.h.
1 day	~ 26.7 N/mm ²
7 days	~ 53.2 N/mm ²
28 days	~ 60.0 N/mm ²

Flexural Strength

(EN 13892-2)

	+23°C / 50% r.h.
1 day	~ 5.5 N/mm ²
7 days	~ 10.3 N/mm ²
28 days	~ 13.0 N/mm ²

Freeze / Thaw / De-Icing Salt Resistance BE II

Resistance factor WFT-L 86% (High)

D - R (SN / VSS 640 461)

Slip Resistance

Slip Resistance Values

(EN 13036-4)

Substrate	SRV Dry	SRV Wet
Sikafloor®-82 EpoCem®	91	71

TRRL Pendulum, Rapra 4S Slider

Abrasion Resistance

10.3 cm³ / 50 cm² and 2.1 mm wear depth (Böhme abrasion)

(EN 13892-3)

Resistance

Chemical Resistance

The Sikafloor® EpoCem® product range has improved chemical resistance over plain concrete in aggressive environments, but is not designed as a chemical protection. For specific chemical resistance, always overcoat with a suitable product from the Sikafloor® and Sikagard® range. For occasional exposure or spillages, consult your local technical department.

System Information

System Structure

The system configuration as described must be fully complied with and may not be changed.

Primer indicated below is suitable for each of these substrates:

Green concrete (as soon as mechanical preparation is possible)

Damp concrete (> 14 days old)

Damp aged concrete (rising moisture)

Patching and repair:

Layer thickness: 7 – 20 mm

Primer : SikaTop®-Armatec®-110 EpoCem®

Mortar Sikafloor®-82 EpoCem® Extended mortar mix. (See mixing for details)

Levelling screed for high substrate roughness:

Layer thickness: 3 - 7 mm

Primer: Sikafloor®-155 WN

Screed: Sikafloor®-82 EpoCem®

Top coat: Suitable product from the Sikafloor® and Sikagard® range

Interlayer priming for Sikafloor®-81/82 EpoCem:

Bonding bridge: Sikafloor®-155 WN

Application Details

Consumption / Dosage

Primer:

Sikafloor®-155 WN (parts A+B), thinned with 10% water, ~ 0.3 - 0.5 kg/m² dependent on the substrate conditions, when repairing monolithic or vacuum concrete, or without a broadcast finish or when Sikafloor®-82 EpoCem® is over-coated with itself.

Extended mortar mix:

Sikafloor®-82 EpoCem® ~ 2.5 - 2.8 kg/m²/mm

Self smoothing screed:

Sikafloor®-82 EpoCem® ~ 2.25 kg/m²/mm

~ 6.75 kg/ m² for a 3 mm thick application (minimum for T.M.B.).

These figures are theoretical and do not allow for any additional material due to surface porosity, surface profile, variations in level or wastage, etc.

Substrate Quality

The concrete substrate must be sound and of sufficient compressive strength (minimum 25 N/mm²) with a minimum pull off strength of 1.5 N/mm².

The substrate can be damp but must be free of standing water and free of all contaminants such as oil, grease, coatings and surface treatments, etc.

If in doubt, apply a test area first

Substrate Preparation

Concrete substrates must be prepared mechanically using abrasive blast cleaning or scarifying equipment to remove cement laitance and achieve an open textured surface.

Weak concrete must be removed and surface defects such as blow holes and voids must be fully exposed.

Repairs to the substrate, filling of blowholes/voids and surface levelling must be carried out using appropriate products from the Sikafloor®, SikaDur® and Sikagard® range of materials.

High spots can be removed by grinding.

All dust, loose and friable material must be completely removed from all surfaces before application of the product, preferably by brush or vacuum.

Application Conditions / Limitations

Substrate Temperature +8°C min. / +30°C max.

Ambient Temperature +8°C min. / +30°C max.

Substrate Moisture Content Can be applied on green or damp concrete, without any standing water.

Although the product can be applied onto green concrete surfaces (> 24 hours), it is advised to allow at least 3 days for early shrinkage of concrete to occur in order to prevent concrete cracks from appearing on the screed surface.

Relative Air Humidity 20% min. / 80% max.

Dew Point Beware of condensation!

The substrate and uncured floor temperature must be at least 3°C above the dew point to reduce the risk of condensation or blooming on the floor finish.

Application Instructions

Mixing

Part A : part B : part C - packing size : 1.00 : 2.50 : 24 kg

Flooring Screed:

At temperatures between +12°C to +25°C:

1 : 2.5 : 20.7 (by weight)

Parts (A+B) : C = 3.5 kg : 24 kg

At temperatures between +8°C to +12°C and +25°C to +30°C:

The amount of part C can be reduced to 24 kg in order to improve workability. Never reduce part C by more than this amount.

1 : 2.5 : 21 (by weight)

Parts (A+B) : C = 3.5 kg : 22 kg

For this application, to achieve a good bond of the mortar to the substrate, SikaTop®-Armatec®-110 EpoCem® must be used as a primer. Apply the mortar wet on wet to the primer.

Mixing Time

Prior to mixing, shake part A (white liquid) briefly until homogenous, then pour into container of part B and shake vigorously for at least 30 seconds. When dosing out of drums, stir and homogenise first.

Pour the mixed binder (A+B) into a suitable mixing container (capacity of about 30 litres) and gradually add part C to the mixer while stirring with a power mixer. Mix thoroughly for 3 minutes until a uniform mix has been achieved with no lumps.

Mix only full units of A+B+C components. Do not mix smaller amounts. Do not add water.

When dosing with additional aggregates, add them after adding Part C to the mix. Mix thoroughly for 3 minutes until a uniform mix has been achieved.

Mixing Tools

Mix using a slow speed electric mixer (300 - 400 rpm) with helical paddle or other suitable equipment.

For mixing 2 – 3 bags at once, single or counter rotating double mortar (basket type) and forced action (pan type) mixers are also recommended. Free fall mixers must not be used.

Application Method / Tools

Place mixed Sikafloor®-82 EpoCem® onto the primed substrate and spread evenly to the required thickness uniformly with a rubber or metal trowel or spatula to and immediately roll with a spike roller to remove entrapped air and obtain an even thickness layer.

Workability can be adjusted by varying slightly the amount of Part C. See "Mixing" above.

Do not use additional water, which would disturb the surface finish and cause discolouration.

A seamless finish can be achieved if a "wet" edge is maintained during application.

Cleaning of Tools

Clean all tools and application equipment with water immediately after use. Hardened / cured material can only be removed mechanically.

Pot life

27.5 kg unit

Temperature / r.h. 75%	Time
+10°C	~ 50 minutes
+20°C	~ 25 minutes
+30°C	~ 12 minutes

**Waiting Time /
Overcoating**

Before applying Sikafloor®-82 EpoCem® on Sikafloor® -155 WN allow:

Substrate temperature	Waiting time	
	Minimum	Maximum
+10°C	12 hours	72 hours
+20°C	6 hours	48 hours
+30°C	4 hours	24 hours

Once Sikafloor®-82 EpoCem® is tack free it is possible to apply vapour permeable seal coats.

Sikafloor®-82 EpoCem® can be over coated with vapour tight coatings when surface humidity falls below 4%! Not earlier than:

Substrate temperature	Waiting time
+10°C	3 days
+20°C	1 day
+30°C	1 day

Note: Successive coats of Sikafloor®-81 / 82 EpoCem® must be applied after priming with Sikafloor®-155 WN and allowing at least the minimum times indicated above between applications.

Times are approximate at 75% r.h. and will be affected by changing and substrate ambient conditions, particularly temperature and relative humidity.

**Notes on Application /
Limitations**

If Sikafloor®-82 EpoCem® is used as TMB (Temporary Moisture Barrier), a minimum layer of 3 mm must be applied. (~ 6.75 kg/m²)

Always ensure good ventilation when using Sikafloor®-82 EpoCem® in a confined space, to remove excess moisture.

Freshly applied Sikafloor®-82 EpoCem® must be protected from damp, condensation and water for at least 24 hours.

Prevent premature drying by protecting from strong wind and do not expose to direct sun light while fresh.

Apply primer and Sikafloor®-82 EpoCem® on a falling temperature. If applied during rising temperatures "pin holing" can occur.

Applications under extreme conditions (high temperature and low humidity) which can cause fast drying of the product must be avoided as the product does not allow the use of curing compounds.

Under no circumstances add water to the mix.

Non moving construction joints require pre-treatment with a stripe coat of primer and Sikafloor®-82 EpoCem®. Treat as follows:

Static Cracks: Prefill and level with SikaDur® or Sikafloor® epoxy resin.

Dynamic Cracks (> 0.4mm): To be assessed on site and if necessary apply a stripe coat of elastomeric material or design as a movement joint.

The incorrect assessment and treatment of cracks can lead to a reduced service life and reflective cracking.

Colour variations can occur on unsealed Sikafloor®-82 EpoCem® through exposure to direct sun light. This however, will not influence the mechanical properties.

When overlaying with PMMA screeds, the surface of Sikafloor®-82 EpoCem® must be fully broadcast with sand 0.4 - 0.7 mm.

The TMB effect in Sikafloor®-EpoCem® is limited in time, without additional preparation.

Always verify the surface moisture content if more than 5-7 days have passed since application.

Curing Details

Applied Product ready for use

Temperature	Foot traffic	Light traffic	Full cure
+10°C	~ 24 hours	~ 3 days	~ 14 days
+20°C	~ 15 hours	~ 2 days	~ 7 days
+30°C	~ 12 hours	~ 1 day	~ 5 days

Note: Times are approximate and will be affected by changing ambient and substrate conditions.

Cleaning / Maintenance

Methods

Due to the texture of its surface, Sikafloor®-82 EpoCem® is not suited to be used as wearing layer where easy staining can occur. A seal coat of the Sikafloor® range with suitable cleaning capabilities is advisable.

Remove dirt using a brush and/or vacuum. Do not use wet cleaning methods until product is fully cured.

Do not use abrasive methods or cleaners.

Value Base

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

Local Restrictions

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

Health and Safety Information

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.

Legal Notes

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

EU Regulation 2004/42 VOC - Decopaint Directive

According to EU-Directive 2004/42, the maximum allowed content of VOC (Product category IIA / Cat. C / Type wb) is, ready for use, 40 g/l (limit 2010). The max. content of Sikafloor®-82 EpoCem®, ready for use, is <40 g/l VOC.



Sika South Africa (Pty) Ltd
9 Hocking Place,
Westmead, 3608
South Africa

E-mail: headoffice@za.sika.com
Phone +27 31 792 6500
Telefax +27 31 700 1760
www.sika.com

