

## PRODUCT DATA SHEET

# Sika BlackSeal® T-130 SG

3 mm thick, torch-on, sheet waterproofing membrane based on APP modified, reinforced bitumen, with sand finish – Flexible to 0°C

### DESCRIPTION

Sika BlackSeal® T-130 SG is a torch applied sheet waterproofing membrane on base of APP- polymerized bitumen, reinforced with Polyester non woven fabric, with a sanded surface and the reverse faced with PE-film to ease installation works

### USES

- As Multilayer System for Water- and damp-proofing of exterior walls of basements against percolating water and soil humidity
- Intermediate layer for Multi-layer Systems for waterproofing of exposed roofs
- As Multi-layer System for waterproofing of ballasted roofs

### CHARACTERISTICS / ADVANTAGES

- Resistant to ageing
- Good tensile strength and elongation
- High resistance to water vapour permeability
- Dimensional stable
- Easy to install by using flame torch method
- Not resistant to root penetration
- Suitable for multi layer installations only
- Must be installed on primed and smooth substrates of concrete or brick walls

### PRODUCT INFORMATION

<b>Packaging</b>	Roll size: 1.00 m (roll width) x 10.00 m (roll length).
<b>Appearance / Colour</b>	Rolled sheet membrane, reinforced with Polyester non woven fabric. Surface: sanded, reverse: PE film to ease installation Membrane thickness: 3.00 mm Colour: black
<b>Shelf Life</b>	4 years from date of production.

<b>Storage Conditions</b>	Store in dry conditions between +5°C to +35°C. Rolls must be stored in their original package, in vertical position and under cool and dry conditions. They must be protected from direct sunlight, rain, snow and ice.	
<b>Length</b>	10.00 m (-1%)	(EN 1848 - 1)
<b>Width</b>	1.00 m (-1%)	(EN 1848 - 1)
<b>Effective Thickness</b>	3.00 mm (± 5%)	(EN 1849 - 1)
<b>Resistance to Impact</b>	≥ 600 mm	(EN 12691)
<b>Tensile Strength</b>	Max 450 N / 50mm (± 20%) 350 N / 50mm (± 20%)	(EN 12311 - 1))
<b>Elongation</b>	Longitudinal / Transversal 40% (± 15%) 40% (± 15%)	(EN 12311 - 1)
<b>Dimensional Stability</b>	Longitudinal / Transversal ≤0.25% ≤0.10%	(EN 1107-1)
<b>Tear Strength</b>	150 N (± 30%) (nail shank)	(EN 12310 -1)
<b>Joint Shear Resistance</b>	≥ 400N / 50 mm	(EN 12317 -1)
<b>Flexibility at low temperature</b>	0°C	(EN 1109)
<b>External Fire Performance</b>	Class F roof (t1-4)	(ENV 1187)
<b>Reaction to Fire</b>	Class F	(EN 13501 - 1)
<b>Flow Resistance</b>	To elevated temperatures: ≥ 110°C	(EN 1110)
<b>Artificial Ageing</b>	<i>No defects</i> Long term exposure to elevated temperatures according to EN 1296 - flexibility at elevated temperatures: >+100°C (from -10°C) By long term exposure to UV radiation and elevated temperatures according to EN 1296 / EN 1297: Max. tensile strength: 400 N / 50 mm, 300 N / 50 mm Max. elongation: 35% Water tightness: ≥ 60 kPa	(EN 1296) (EN 1110) (EN 12311 - 1) (EN 12311 - 1) (EN 1928)
<b>Water Vapour Transimission</b>	μ ≥ 20'000	(EN 1931)
<b>Water Tightness</b>	≥ 60 kPa	(EN 1928 - B)

## SYSTEM INFORMATION

<b>System Structure</b>	Ancillary Product: Sika® BlackSeal-Primer
-------------------------	----------------------------------------------

## APPLICATION INFORMATION

<b>Ambient Air Temperature</b>	+5°C min. / +35°C max
<b>Relative Air Humidity</b>	80% max.
<b>Substrate Temperature</b>	+5°C min. / +35°C max
<b>Substrate Moisture Content</b>	No visible moisture

## APPLICATION INSTRUCTIONS

### SUBSTRATE QUALITY

*Concrete / brickwork / mortar screeds:*

Clean, sound and dry, homogeneous, free from oils and grease, dust and loose or friable particles. Horizontal surfaces must be sloped > 1.5%

### SUBSTRATE PREPARATION

#### APPLICATION METHOD / TOOLS

Primer application on substrate for first membrane layer:

Application of Sika® BlackSeal Primer for first membrane layer. Application by brush, roller, or airless spraying. Waiting time, depending to temperature, complete evaporation. Priming for second and further membrane layers not required.

Installation method:

Fully bonded to substrate by torch-on method with Propane - gas flame. Unrolling and positioning of membrane roll with PE-film faced to substrate. Rolling of half roll length, heating of membrane reverse with gas flame until melting of PE-film and bitumen mass while continuous unrolling. A bead of liquid bitumen must be visible on underside of roll. The torch-on membrane must be firmly pressed to substrate in order to avoid air entrapments either with roller or heavy broom. Repeat procedure with second half of roll length.

All installed membranes must be sufficiently overlapped. Sidelaps: 80 – 100 mm, Endlaps: 120 – 150 . The seams must be finished with roller while installing of membranes to close gaps and capillaries.

## FURTHER DOCUMENTS

This product shall only be used by installers, skilled and experienced in installation of bituminous membranes.

Avoid damage on installed membrane while over torch of further sheet membrane

The water tightness of the structure must be tested and approved after completion of the membrane installation works according to the requirements of the client's specifications.

## BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

#### Sika South Africa (Pty) Ltd

9 Hocking Place,  
Westmead, 3608  
South Africa  
Phone +27 31 792 6500  
www.sika.co.za



#### Product Data Sheet

Sika BlackSeal® T-130 SG  
September 2020, Version 01.02  
020920011990000140

## LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

## ECOLOGY HEALTH AND SAFETY

### LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request. It may be necessary to adapt the above disclaimer to specific local laws and regulations. Any changes to this disclaimer may only be implemented with permission of Sika® Corporate Legal in Baar.

SikaBlackSealT-130SG-en-ZA-(09-2020)-1-2.pdf