

BUILDING TRUST

PRODUCT DATA SHEET

SikaGrout[®] GP

General purpose, shrinkage-compensated cementitious grout

DESCRIPTION

SikaGrout[®] GP is a shrinkage-compensated, flowable cementitious grout with extended working time to suit local ambient temperatures.

USES

SikaGrout[®] GP is a general purpose grout suitable for the following applications:

- Machine base plates
- Column base plates
- Filling of cavities, gaps, recesses, etc.
- Concrete repairs (pre-packed grouting)

PRODUCT INFORMATION

CHARACTERISTICS / ADVANTAGES

- Easy to mix and apply
- Flowable consistency (according to mix)
- Non-corrosive
- Non-toxic
- Iron and chloride free
- Shrinkage-compensated
- Good pumping properties

Packaging	25 kg bag		
Shelf Life	12 months from the date of production		
Storage Conditions	Store properly in original, unopened and undamaged sealed packaging in dry conditions at temperatures between +10 °C and +35 °C. Protect from direct sunlight.		
Appearance / Colour	Grey premixed powder		
Maximum Grain Size	2.4 mm		
Density	~2.25 kg/l (depending on consistency and temperature)		

TECHNICAL INFORMATION

ours	> 10 N/mm²	(ASTM C 109)
ours	> 20 N/mm ²	
ys	> 40 N/mm²	
ays	> 60 N/mm ²	
	ours ys ays	ours > 20 N/mm² ys > 40 N/mm²

APPLICATION INFORMATION

Yield

Flowable consistency

	SikaGrout [®] GP	Water		Volume Mortar	
	2.25 kg	0.36 L		1 L	
	25 kg	4.0 L		12.0 L	
	84 x 25 kg bag	336 L		1 m ³	
	Pourable consistend	cy .			
	SikaGrout [®] GP	Water		Volume Mortar	
	2.35 kg	0.282 L		1 L	
	25 kg	3.0 L		11.0 L	
	91 x 25 kg bag	273 L		1 m ³	
Layer Thickness	Minimum 10 mm / Maximum 100 mm				
Flowability	Flowable consistence	cy			
	≥ 270 mm (at 3 min	s)		(EN 1015-3)	
Ambient Air Temperature	+10 °C min. / +40 °C max.				
Mixing Ratio	Consistency		Water (L) per 25 kg of grout		
	Flowable		3.5–4.0		
	Pourable		3.2–3.5		
	These mix ratios are a guide and preliminary trials at local temperatures / humidity conditions are recommended.				
Substrate Temperature	+10 °C min. / +40 °C max.				

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LIMITATIONS

At temperatures +20 °C and below, setting time and strength development will be slower.

Non-shrink grout contains additives which expand either during the plastic stage and / or the hardening stage to compensate for the shrinkage of the cementitious matrix. However, this 'non-shrink' property will be effective only if the material is not subjected to water loss.

This is confirmed by a note in the ASTM C 1107 Standard Specification for packaged dry, hydraulic cement grout (non-shrinkable), which clarifies the behaviour of the non-shrink grout when subjected to some drying:

"Note 1: Since all conditions of use cannot be anticipated, this specification requires non-shrink grout to exhibit no shrinkage when tested in a laboratory controlled moist-cured environment, and requires only the reporting of the observed height change, usually shrinkage, when test specimens are subject to some degree of drying."

ECOLOGY HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY / PRE-TREATMENT

The substrate should be prepared by suitable mechanical preparation techniques such as high pressure water, breakers, grit blasting, scabblers, etc. All absorbent surfaces must be well saturated with clean water, but free of any surface water or puddles prior to the application of SikaGrout[®] GP.

Concrete, mortar and stone

Surfaces must be sound, clean, free from frost, oils, grease, standing water and all loosely adhering particles and other surface contaminants.

Metal surfaces (iron and steel)

Surfaces should be clean, free from scale, rust, oil and grease.

MIXING

Place about 70–80 % of the premeasured clean water (depending on consistency required – refer to "Mix Ratio") into a clean container and gradually add the whole bag of SikaGrout[®] GP into it while continuously mixing. Add the remaining water until the desired consistency is obtained.

Mix for 2–3 minutes with a low speed drill (500 rpm max.).

BUILDING TRUST

Product Data Sheet SikaGrout® GP July 2024, Version 01.08 020201010010000085



APPLICATION

After mixing, stir lightly with a spatula for a few seconds to release any entrapped air. The grout is then poured immediately into the prepared formwork. When carrying out baseplate grouting, ensure sufficient pressure head is maintained for uninterrupted mortar flow. For formwork repair, the prepared formwork must be firmly in place and kept watertight. When placing grout over a large area, it is important to maintain a continuous flow throughout. Work sequence must be properly organised to ensure an uninterrupted flow. In large areas, SikaGrout® GP may be pumped using heavy duty diaphragm pumps. Screw feed and piston pumps may also be used.

Specific Areas of Application

pourable consistency		
flowable / pourable con-		
sistency		
flowable consistency		

Grouting large volumes

For sections thicker than 100 mm, it is necessary to fill SikaGrout[®] GP with graded 10 mm silt free aggregates to minimise temperature rise generated during the curing stage. The quantity of aggregates should not exceed 1 part aggregates to 1 part SikaGrout[®] GP by weight. For such mixes, a conventional concrete mixer and pump may be used. To further ensure that air entrapped during mixing is allowed to fully escape, it may be necessary to make breather holes. Use steel rods or chains to assist the flow of grout where necessary. Preliminary trials are recommended.

CURING TREATMENT

When formwork type repair is used, leave the formwork in place for at least 3 days.

Upon removal of the formwork, cure the exposed surfaces immediately with Antisol[®] curing compound or use other approved curing methods.

CLEANING OF TOOLS

Clean all tools and application equipment with water immediately after use. Hardened or cured material can only be mechanically removed.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika South Africa (Pty) Ltd 9 Hocking Place, Westmead, 3608 South Africa Phone +27 31 792 6500 www.sika.co.za



Product Data Sheet SikaGrout® GP July 2024, Version 01.08 020201010010000085 SikaGroutGP-en-ZA-(07-2024)-1-8.pdf

BUILDING TRUST

